

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6 : B01D 15/04, 53/02, B01J 8/00, 5/02, 19/08, 20/00, 20/02, 20/10, 20/20, 23/00, 23/02, 23/32, 23/70, 29/06, 37/34, C01B 7/00, 17/16, 53/00, C02F 1/42, C07C 1/00	A1	(11) International Publication Number: WO 98/17365 (43) International Publication Date: 30 April 1998 (30.04.98)
(21) International Application Number: PCT/US97/18729 (22) International Filing Date: 21 October 1997 (21.10.97) (30) Priority Data: 08/734,329 21 October 1996 (21.10.96) US (71) Applicant: PROJECT EARTH INDUSTRIES, INC. [US/US]; Suite 1900, 945 East Paces Ferry Road, Atlanta, GA 30326 (US). (72) Inventors: MOSKOVITZ, Mark, L.; P.O. Box 80402, Atlanta, GA 30366-0402 (US). KEPNER, Bryan, E.; 1110 The Valley, Atlanta, GA 30328 (US). (74) Agents: KATZ, Mitchell, A. et al.; Needle & Rosenberg, 127 Peachtree Street, N.E., Atlanta, GA 30303 (US).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG, ZW), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: ENHANCED ADSORBENT AND ROOM TEMPERATURE CATALYST PARTICLE AND METHOD OF MAKING AND USING THEREFOR		
(57) Abstract A method for producing an enhanced adsorbent and/or enhanced catalytic particle and/or for producing a catalytic particle, comprising the steps of: (a) removing an effective amount of air from a closed chamber containing an adsorbent and/or catalytic particle, wherein the resultant chamber pressure is less than one atmosphere; (b) raising the chamber pressure with an inert gas to at least one atmosphere; (c) contacting the particle with an energy beam of sufficient energy for a sufficient time to thereby enhance the adsorbent and/or catalytic properties of the particle and/or produce catalytic properties in the particle. A continuous process directed to step (c) alone is also provided. Also disclosed are adsorbent and/or catalytic particles, methods of contaminant reduction or elimination, including room temperature catalysis, particle binders, apparatuses of the present invention, and methods of increasing the surface area of adsorbent and/or catalytic particles.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

**ENHANCED ADSORBENT AND ROOM TEMPERATURE
CATALYST PARTICLE AND
METHOD OF MAKING AND USING THEREFOR**

5

BACKGROUND OF THE INVENTION

CROSS REFERENCE TO RELATED APPLICATIONS

10 This application is (1) a continuation-in-part of PCT/US96/05303, filed April 17, 1996, pending, which is a continuation-in-part of U.S. application serial No. 08/426,981, filed April 21, 1995, pending and (2) a continuation-in-part of U.S. application serial No. 08/426,981, filed April 21, 1995, pending. All of the above applications are hereby incorporated by this reference in their entireties for all of their teachings.

15

FIELD OF THE INVENTION

20 This invention relates generally to adsorbent particles that have improved adsorbent properties and/or improved or newly existing catalytic properties, including room temperature catalytic capability.

BACKGROUND ART

25 Oxides of metals and certain non-metals are known to be useful for removing contaminants from a gas or liquid stream by adsorption mechanisms. For example, the use of activated alumina is considered to be an economical method for treating water for the removal of a variety of pollutants, gasses, and some liquids. Its highly porous structure allows for preferential adsorption capacity for moisture and contaminants contained in gasses and some
30 liquids. It is useful as a desiccant for gasses and vapors in the petroleum industry, and has also

been used as a catalyst or catalyst-carrier in air and in water purification. Removal of contaminants such as phosphates by activated alumina are known in the art. See, for example, Yee, W., "Selective Removal of Mixed Phosphates by Activated Alumina," *J. Amer. Waterworks Assoc.*, Vol. 58, pp. 239-247 (1966).

5

U.S. Patent No. 5,242,879 to Abe *et al.* discloses that activated carbon materials, which have been subjected to carbonization and activation treatments, and then further subjected to an acid treatment and a heat treatment in an atmosphere comprising an inert gas or a reducing gas, have a high catalytic activity and are suitable as catalysts for the decomposition of hydrogen peroxide, hydrazines or other water pollutants such as organic acids, quaternary ammonium-salts, and sulfur-containing compounds. Acid is used to remove impurities and not to enhance the adsorbent features.

10

Ion implantation has been used in integrated circuit fabrication. U.S. Patent No. 4,843,034 to Herndon *et al.* discloses methods and systems for fabricating interlayer conductive paths in integrated circuits by implanting ions into selected regions of normally insulative layers to change the composition and/or structure of the insulation in the selected regions. It is stated that a wide range of insulative materials can be rendered selectively conductive, including polymeric insulators and inorganic insulators, such as metal or semiconductor oxides, nitrides or carbides. Insulators which can be processed according to this patent include silicone dioxide, silicon nitride, silicon carbide, aluminum oxides, and others. It is disclosed that implanted ions can include ions of silicon, germanium, carbon, boron, arsenic, phosphorous, titanium, molybdenum, aluminum, and gold. Typically, the implantation energy varies from about 10 to about 500 KeV. It is disclosed that the ion implantation step changes the composition and structure of the insulative layer and is believed also to have the effect of displacing oxygen, nitrogen, or carbon so as to promote the migration and alloying of metal from the conductive layer(s) into the implanted region during the sintering step. The implantation also is believed to have the physical effect of disrupting the crystal lattice, which may also facilitate the fusion of the metal. This results in a composite material in the implantation region essentially consisting of the disruptive (disrupted) insulator and implanted

20

25

30

ions. In the working examples, ions of silicon were implanted into the particular region of the silicon dioxide layer using a direct implantation machine.

U.S. Patent No. 5,218,179 to Matossian *et al.* discloses a plasma source arrangement for providing ions for implantation into an object. A large scale object which is to be
5 implanted with ions is enclosed in a container. The plasma is generated in a chamber which is separate from, and opens into the container for a plasma source ion implantation working volume. The plasma diffuses from the chamber into the container to surround the object with substantially improved density compared to conventional practice. High voltage negative pulses are applied to the object, causing the ions to be accelerated from the plasma toward and
10 be implanted into the object.

Thus, there has been a need in the art for adsorbents that have improved ability to adsorb particular materials, especially contaminants from a gas or liquid stream, to thereby purify the stream. Also, there has been a need in the art for catalysts that have the ability or
15 that have an improved ability to catalyze the reaction of contaminants into non-hazardous products.

Additionally, there has been a need in the art for adequately agglomerating adsorbent particles together to form a composite particle for performing simultaneous multiple
20 adsorptions and purifications. Prior art particles typically mask at least some of the adsorbent or catalytic sites on the particles, thus reducing the efficiency or performance of the particles.

In the present invention, none of the above-cited documents discloses compounds, compositions or processes such as those described and claimed herein.

25

SUMMARY OF THE INVENTION

In accordance with the purpose(s) of this invention, as embodied and broadly described herein, this invention, in one aspect, relates to a method for producing an enhanced adsorbent
30 and/or enhanced catalytic particle and/or for producing a catalytic particle, comprising the

steps of:

- (a) removing an effective amount of air from a closed chamber containing an adsorbent and/or catalytic particle, wherein the resultant chamber pressure is less than one atmosphere;
- (b) raising the chamber pressure with an inert gas to at least one atmosphere;
- 5 (c) contacting the particle with an energy beam of sufficient energy for a sufficient time to thereby enhance the adsorbent and/or catalytic properties of the particle and/or produce catalytic properties in the particle.

10 The particle produced from this process can catalytically decompose particular contaminants, even at room temperature.

The invention further provides a method for producing an enhanced adsorbent and/or enhanced catalytic particle and/or for producing a catalytic particle, comprising implanting oxygen into an adsorbent and/or catalytic particle.

15

In yet another aspect, the invention relates to the particle made by the process of the invention.

20 In yet another aspect, the invention relates to an enhanced adsorbent and/or enhanced catalytic particle and/or a catalytic particle comprising an adsorbent particle that has been treated to provide an excess of oxygen implanted at least on the surface of the particle to thereby form an enhanced adsorbent and/or enhanced catalytic particle and/or a catalytic particle.

25 In yet another aspect, the invention relates to a binder for binding adsorbent and/or catalytic particles to produce an agglomerated particle comprising colloidal aluminum oxide and an acid.

30 In yet another aspect, the invention relates to a method for binding adsorbent and/or catalytic particles, comprising the steps of:

- (a) mixing colloidal aluminum oxide with the particles and an acid;
- (b) agitating the mixture to homogeneity; and
- (c) heating the mixture for a sufficient time to cause cross-linking of the aluminum oxide in the mixture.

5 In yet another aspect, the invention relates to a method for reducing or eliminating the amount of a contaminant from a liquid or gas stream comprising contacting the particle of the invention with the contaminant in the stream for a sufficient time to reduce or eliminate the amount of the contaminant from the stream.

10 In yet another aspect, the invention relates to a method for adsorbing a contaminant from a liquid or gas stream onto an adsorbent particle comprising contacting the particle of the invention with the contaminant in the stream for a sufficient time to adsorb the contaminant.

15 In yet another aspect, the invention relates to a method for catalyzing the degradation of a hydrocarbon comprising contacting the hydrocarbon with the particle of the invention for a sufficient time to catalyze the degradation of the hydrocarbon.

20 In yet another aspect, the invention relates to a method for reducing or eliminating the amount of a contaminant from a gas stream by catalysis comprising contacting the particle of the invention with a gas stream containing a contaminant comprising an oxide of nitrogen, an oxide of sulfur, carbon monoxide, or mixtures thereof for a sufficient time to reduce or eliminate the contaminant amount.

25 In yet another aspect, the invention relates to an apparatus for producing an enhanced adsorbent and/or enhanced catalytic particle and/or for producing a catalytic particle comprising:

- (a) chamber means for containing the particle in a closed system having an inlet gas port, an exit gas port, and a target plate, said chamber means being capable of
- 30 maintaining vacuum and positive pressures;

- (b) means for providing an inert gas to the chamber means through the inlet gas port;
- (c) means for withdrawing from the chamber means an effective amount of the ambient air therein so as to create a vacuum within the chamber means; and
- (d) means for providing an energy beam to the chamber means, said energy beam means outlet being targeted at the target plate.

In yet another aspect, the invention relates to a method for increasing the surface area of an adsorbent and/or catalytic particle, comprising the steps of

- (a) raising the chamber gauge pressure of a closed chamber containing the adsorbent and/or catalytic particle to at least 100 psi with an inert gas and
- (b) rapidly reducing the chamber pressure to thereby increase the surface area of the particle.

In yet another aspect, the invention relates to a method for producing an enhanced adsorbent and/or enhanced catalytic particle and/or for producing a catalytic particle, comprising the step of:

- (a) contacting an adsorbent and/or catalytic particle with an energy beam of sufficient energy for a sufficient time to thereby enhance the adsorbent and/or catalytic properties of the particle and/or produce catalytic properties in the particle.

Additional advantages of the invention will be set forth in part in the description which follows, and in part will be obvious from the description, or may be learned by practice of the invention. The advantages of the invention will be realized and attained by means of the elements and combinations particularly pointed out in the appended claims. It is to be understood that both the foregoing general description and the following detailed description are exemplary and explanatory only and are not restrictive of the invention, as claimed.

The accompanying drawings, which are incorporated in and constitute a part of this specification, illustrate several embodiments of the invention and together with the description,

serve to explain the principles of the invention:

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 shows an apparatus of one embodiment of the present invention for producing
5 an enhanced adsorbent and/or enhanced catalytic particle and/or for producing a catalytic
particle.

Fig. 2 is a graph showing the reduction of NO concentration using a particle of the
10 invention.

Fig. 3 is a graph showing the reduction of CO concentration using a particle of the
invention.

Fig. 4 is a graph showing the reduction of NO concentration using a particle that is not
15 part of the present invention.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

The present invention may be understood more readily by reference to the following
20 detailed description of preferred embodiments of the invention and the Examples included
therein and to the Figures and their previous and following description.

Before the present compositions of matter, methods, and apparatuses are disclosed and
described, it is to be understood that this invention is not limited to specific synthetic methods,
25 to particular formulations, or to particular apparatuses, as such may, of course, vary. It is also
to be understood that the terminology used herein is for the purpose of describing particular
embodiments only and is not intended to be limiting.

It must be noted that, as used in the specification and the appended claims, the singular
30 forms "a," "an" and "the" include plural referents unless the context clearly dictates otherwise.

In this specification and in the claims which follow, reference will be made to a number of terms which shall be defined to have the following meanings:

"Optional" or "optionally" means that the subsequently described event or circumstance may or may not occur, and that the description includes instances where said event or circumstance occurs and instances where it does not.

The term "particle" as used herein is used interchangeably throughout to mean a particle in the singular sense or a combination of smaller particles that are grouped together into a larger particle, such as an agglomeration of particles.

The term "ppm" refers to parts per million and the term "ppb" refers to parts per billion. GPM is gallons per minute.

In accordance with the purpose(s) of this invention, as embodied and broadly described herein, this invention, in one aspect, relates to a method for producing an enhanced adsorbent and/or enhanced catalytic particle and/or for producing a catalytic particle, comprising the steps of:

- (a) removing an effective amount of air from a closed chamber containing an adsorbent and/or catalytic particle, wherein the resultant chamber pressure is less than one atmosphere;
- (b) raising the chamber pressure with an inert gas to at least one atmosphere;
- (c) contacting the particle with an energy beam of sufficient energy for a sufficient time to thereby enhance the adsorbent and/or catalytic properties of the particle and/or produce catalytic properties in the particle.

The particle produced from this process can catalytically decompose particular contaminants at room temperature.

The invention further provides a method for producing an enhanced adsorbent and/or enhanced catalytic particle and/or for producing a catalytic particle, comprising implanting

oxygen into an adsorbent and/or catalytic particle.

In yet another aspect, the invention relates to the particle made by the process of the invention.

5 In yet another aspect, the invention relates to an enhanced adsorbent and/or enhanced catalytic particle and/or a catalytic particle comprising an adsorbent particle that has been treated to provide an excess of oxygen implanted at least on the surface of the particle to thereby form an enhanced adsorbent and/or enhanced catalytic particle and/or a catalytic particle.

10 In yet another aspect, the invention relates to a binder for binding adsorbent and/or catalytic particles to produce an agglomerated particle comprising colloidal aluminum oxide and an acid.

15 In yet another aspect, the invention relates to a method for binding adsorbent and/or catalytic particles, comprising the steps of:

- (a) mixing colloidal aluminum oxide with the particles and an acid;
 - (b) agitating the mixture to homogeneity; and
 - (c) heating the mixture for a sufficient time to cause cross-linking of the aluminum
- 20 oxide in the mixture.

In yet another aspect, the invention relates to a method for reducing or eliminating the amount of a contaminant from a liquid or gas stream comprising contacting the particle of the invention with the contaminant in the stream for a sufficient time to reduce or eliminate the

25 amount of the contaminant from the stream.

In yet another aspect, the invention relates to a method for adsorbing a contaminant from a liquid or gas stream onto an adsorbent particle comprising contacting the particle of the invention with the contaminant in the stream for a sufficient time to adsorb the contaminant.

30

In yet another aspect, the invention relates to a method for catalyzing the degradation of a hydrocarbon comprising contacting the hydrocarbon with the particle of the invention for a sufficient time to catalyze the degradation of the hydrocarbon.

5 In yet another aspect, the invention relates to a method for reducing or eliminating the amount of a contaminant from a gas stream by catalysis comprising contacting the particle of the invention with a gas stream containing a contaminant comprising an oxide of nitrogen, an oxide of sulfur, carbon monoxide, or mixtures thereof for a sufficient time to reduce or eliminate the contaminant amount.

10 In yet another aspect, the invention relates to an apparatus for producing an enhanced adsorbent and/or enhanced catalytic particle and/or for producing a catalytic particle comprising:

- 15 (a) chamber means for containing the particle in a closed system having an inlet gas port, an exit gas port, and a target plate, said chamber means being capable of maintaining vacuum and positive pressures;
- (b) means for providing an inert gas to the chamber means through the inlet gas port;
- (c) means for withdrawing from the chamber means an effective amount of the ambient air therein so as to create a vacuum within the chamber means; and
- 20 (d) means for providing an energy beam to the chamber means, said energy beam means outlet being targeted at the target plate.

In yet another aspect, the invention relates to a method for increasing the surface area of an adsorbent and/or catalytic particle, comprising the steps of

- 25 (a) raising the chamber gauge pressure of a closed chamber containing the adsorbent and/or catalytic particle to at least 100 psi with an inert gas and
- (b) rapidly decompressing the chamber pressure to thereby increase the surface area of the particle.

30 In yet another aspect, the invention relates to a method for producing an enhanced

adsorbent and/or enhanced catalytic particle and/or for producing a catalytic particle, comprising the step of:

- (a) contacting an adsorbent and/or catalytic particle with an energy beam of sufficient energy for a sufficient time to thereby enhance the adsorbent and/or catalytic properties of the particle and/or produce catalytic properties in the particle.

By enhanced adsorbent and/or enhanced catalytic particle, it is understood that the particles of this invention have improved adsorbent and/or improved catalytic properties over prior art adsorbent and/or catalytic particles. Also, by producing a catalytic particle, it is understood that some particles of the instant invention have catalytic properties for catalyzing the conversion of particular contaminants into other forms, whereas the same particles not treated by the process of the present invention possess no catalytic properties at least for those particular contaminants.

Enhanced adsorptive properties is intended to include both ion capture and ion exchange mechanisms. Ion capture refers to the ability of the particle to irreversibly bond to other atoms through ionic or covalent interactions. Ion exchange is well known in the art and refers to ions being interchanged from one substance to another. Adsorption is a term well known in the art and should be distinguished from absorption.

In the particle of this invention, typically any particle that initially has some adsorbent and/or catalytic properties can be used. For example, activated carbon and oxide particles can be oxygen implanted by the process of the present invention.

The invention contemplates the use of any prior art adsorbent and/or catalyst particle or composite particle of two or more types of particles. In a preferred embodiment, the particle comprises an oxide particle, preferably a metal oxide particle, and even more preferably a non-ceramic, porous metal oxide particle. Examples of such particles include, but are not limited to, oxide complexes, such as transition metal oxides, lanthanide oxides, thorium oxide, as well as oxides of Group IIA (Mg, Ca, Sr, Ba), Group IIIA (B, Al, Ga, In, Tl),

Group IVA (Si, Ge, Sn, Pb), and Group VA (As, Sb, Bi). In another embodiment, the particle comprises an oxide of aluminum, titanium, copper, vanadium, silicon, manganese, iron, zinc, zirconium, tungsten, rhenium, arsenic, magnesium, thorium, silver, cadmium, tin, lead, antimony, ruthenium, osmium, cobalt or nickel or zeolite. Typically, any oxidation state of the oxide complexes may be useful for the present invention. The oxide can be a mixture of at least two metal oxide particles having the same metal with varying stoichiometry and oxidation states. In one embodiment, the particle comprises Al_2O_3 , TiO_2 , CuO , Cu_2O , V_2O_5 , SiO_2 , MnO_2 , Mn_2O_3 , Mn_3O_4 , ZnO , WO_2 , WO_3 , Re_2O_7 , As_2O_3 , As_2O_5 , MgO , ThO_2 , Ag_2O , AgO , CdO , SnO_2 , PbO , FeO , Fe_2O_3 , Fe_3O_4 , Ru_2O_3 , RuO_4 , OsO_4 , Sb_2O_3 , CoO , Co_2O_3 , NiO or zeolite. In a further embodiment, the particle further comprises a second type of adsorbent and/or catalyst particles of an oxide of aluminum, titanium, copper, vanadium, silicon, manganese, iron, zinc, zirconium, tungsten, rhenium, arsenic, magnesium, thorium, silver, cadmium, tin, lead, antimony, ruthenium, osmium, cobalt or nickel or zeolite, activated carbon, including coal and coconut carbon, peat, zinc or tin. In another embodiment, the particle further comprises a second type of adsorbent and/or catalyst particles of aluminum oxide, titanium dioxide, copper oxide, vanadium pentoxide, silicon dioxide, manganese dioxide, iron oxide, zinc oxide, zeolite, activated carbon, peat, zinc or tin particle. In a preferred embodiment, the particle comprises non-amorphous, non-ceramic, crystalline, porous, calcined aluminum oxide that was produced by calcining the precursor to the calcined aluminum oxide at a particle temperature of from 400°C to 700°C , preferably in the gamma, chi-rho, or eta form. The precursor to calcined aluminum oxide can include but is not limited to boehmite, bauxite, pseudo-boehmite, scale, $\text{Al}(\text{OH})_3$ and alumina hydrates. In the case of other metal oxide complexes, these complexes can also be calcined or uncalcined.

In another embodiment, for oxide particles, oxides of metals or oxides of non-metals, such as silicon or germanium, are preferred. Even more preferred are oxides of transition metals, oxides of metals of Group III (B, Al, Ga, In, Tl) and IA (Li, Na, K, Rb, Cs, Fr) of the periodic table, and oxides of silicon. Even more preferred are oxides of aluminum, titanium, copper, vanadium, silicon, manganese, iron, zinc, titanium and zeolite. Particularly preferred oxides include aluminum oxide (Al_2O_3), silicon dioxide (SiO_2), manganese dioxide (MnO_2), copper oxide (CuO), iron oxide black (Fe_3O_4), iron oxide red (ferric oxide or Fe_2O_3), zinc

oxide (ZnO), zirconium oxide (ZrO₂), vanadium pentoxide (V₂O₅), titanium dioxide (TiO₂) and zeolite. Typical zeolites used in the present invention include "Y" type, "beta" type, mordenite, and ZSM5.

In one embodiment, the particle comprises aluminum oxide that has been pre-treated by a calcination process. Calcined aluminum oxide particles are well known in the art. They are particles that have been heated to a particular temperature to form a particular crystalline structure. Processes for making calcined aluminum oxide particles are well known in the art as disclosed in, e.g., *Physical and Chemical Aspects of Adsorbents and Catalysts*, ed. Linsen *et al.*, Academic Press (1970), which is incorporated by reference herein. In one embodiment, the Bayer process can be used to make aluminum oxide precursors. Also, pre-calcined aluminum oxide, that is, the aluminum oxide precursor (Al(OH)₃), and calcined aluminum oxide are readily commercially available. Calcined aluminum oxide can be used in this dried form or can be used in a partially or near fully deactivated form by allowing water to be adsorbed onto the surface of the particle.

In a preferred embodiment, the aluminum oxide has been produced by calcining at a temperature of from 400°C to 700°C. These calcined aluminum oxide particles are preferably in the gamma, chi-rho, or eta forms and have a pore size of from 3.5 nm to 35 nm diameter and a BET surface area of from 120 to 350 m²/g.

For activated carbon, any of the activated carbons useful in the adsorbent art can be used. Preferably coal based carbon or coconut based carbon are used. Generally, coal based carbon can be used to remediate aqueous contaminants while coconut based carbon can be used to remediate airborne or gaseous contaminants. Preferably, the activated carbon is less than 20 microns in size for ease of mixing and extrusion.

The particle of the invention can be used alone, in combination with identical or different type composition particles prepared by the processes of the invention, and/or in combination with other adsorbent or catalytic particles known in the art. The particles can be combined in a physical mixture or agglomerated using techniques known in the art or

disclosed herein. In a preferred embodiment, different composition type particles are combined by agglomeration to form a multifunctional composite particle. In this embodiment, particles can be used to achieve multiple functions simultaneously, such as by removing multiple contaminants, by taking advantage of the individual effects from each of the types of particles. Co-particles that are preferably used in this invention include all particles previously disclosed and zeolite. The quantity and proportions of each component vary depending on the contaminant being remediated.

In one embodiment, the composite particle comprises aluminum oxide and a second particle of titanium dioxide, copper oxide, vanadium pentoxide, silicon dioxide, manganese dioxide, iron oxide, zinc oxide, activated carbon, or zeolite. In another embodiment, the composite particle comprises aluminum oxide and activated carbon. In another embodiment, the particle comprises activated carbon (coal-based), activated carbon (coconut-based), silicon dioxide, and aluminum oxide. In a preferred embodiment, this particle is used to remediate aqueous contamination. In one embodiment, this particle of coal-based activated carbon, coconut-based activated carbon, silicon dioxide, and aluminum oxide is used to remediate aqueous contaminants, such as 1,2-dibromo-3-chloropropane (DBCP), radon, and heavy metals, from a contaminated water source.

The particles of this invention can be subjected to other treatments prior to or after being treated by the process of the present invention. The particles of the invention can be pretreated by processes known in the art to improve their adsorptive capability, such as by calcination. Calcination refers to heating a solid to a temperature below its melting point to alter the crystal structure to a particular form. The calcined particle can be dried or maintained in dry form creating an activated particle or, if water is absorbed on the particle, the particle can be partially or near fully deactivated.

The adsorbent, catalyst, and adsorbent and catalyst particles used in this invention can be additionally enhanced by other processes, such as, for example, the particles can be dried to be activated or can be treated by processes disclosed in the prior filed parent applications of and in applicants' copending application filed on the same date as this application and entitled

“Acid Contacted Enhanced Adsorbent Particle and Method of Making and Using Therefor,” which is a continuation-in-part of U.S. application serial No. 08/662,331, filed June 12, 1996, pending, which is a continuation-in-part of PCT/US95/15829, filed June 12, 1995, pending, which is a continuation-in-part of U.S. application serial No. 08/351,600, filed December 7, 1994, abandoned, the disclosures of the above application filed on the same date as this application and all of its prior filed priority applications are herein incorporated by this reference in their entireties for all of their teachings.

In one embodiment, the particles of this invention can be in dry, slurry, or gel form. The particle size can vary depending on the end use, ranging in sizes known in the art, such as colloidal, microscopic, or macroscopic. Preferably, the particles prior to agglomeration are less than 20 microns in size for ease of mixing and extrusion. The particle size after agglomeration can vary depending on the application. In large columns, the particle size can be as large as one inch in diameter. The size range is typically from 200 microns to 3000 microns, preferably from 500 microns to 1500 microns.

Binders for binding the individual particles to form an agglomerated particle are known in the art or are described herein. In a preferred embodiment, the binder can also act as an adsorbent and/or a catalyst. Preferred binders are disclosed in applicants' application filed on the same date as this application entitled “Adsorbent and/or Catalyst and Binder System and Method of Making and Using Therefor,” the disclosure of which is herein incorporated by this reference in its entirety for all of its teachings.

A preferred binder for the agglomerated particle is colloidal alumina or colloidal silica. The colloidal aluminum oxide goes through a transformation stage and cross-links with itself from 25°C to 400°C, preferably 250°C and/or can cross-link with the particle. Colloidal silicon dioxide cross-links with itself if it is sufficiently dried to remove water typically at temperatures of from 25°C to 400°C. Preferably, from about 1 to 99.9 by weight, or 20% to 99% by weight, of the total mixture is colloidal aluminum oxide or colloidal silicon dioxide to provide the necessary crosslinking during heating to bind the agglomerated particle into a water-resistant particle. The particle can then withstand exposure to all types of water for an

extended time and not disintegrate.

The binder can be mixed with the particle before or after the ion or electron energy treatment of this invention. In one embodiment, the agglomerated particle is made by mixing colloidal aluminum oxide with the adsorbent particles. Typically, from about 1 to about 5 99.9% by weight, or from 20 to 99% by weight of the mixture is colloidal aluminum oxide. The particle mixture is then mixed with an acid solution such as, for example, nitric, sulfuric, hydrochloric, boric, acetic, formic, phosphoric, and mixtures thereof. In one embodiment the acid is 5% nitric acid solution. The colloidal aluminum oxide, adsorbent and/or catalytic particles, and acid solution are thoroughly mixed so as to create a homogenous blend of all 10 elements. Then additional acid solution is added and further mixing is performed until the mixture reaches a suitable consistency for agglomeration. After agglomeration is complete, the agglomerated particles are heated to cause the colloidal aluminum oxide crosslinking to occur.

15 Sources and/or methods of making the starting materials for the various adsorbent particles of the present invention are readily available and are well-known to those of ordinary skill in the art.

For an explanation of the process used to make a particle of one embodiment of this 20 invention, reference is made to Figure 1. The apparatus of this embodiment is designated generally as 10. The particulate material or target media 20 to be treated is placed in a chamber 11 on an ungrounded target plate 22. In one embodiment, the target plate can be rotated to provide more efficient treatment of the particle by the energy beam. Chamber 11 is preferably made of a dielectric material. Chamber 11 is sealed by a compression plate latched 25 door 12 that has the ability to withstand pressure differentials ratios both in the positive as well as negative pressures. Pressure is monitored with pressure gauge 18. Vacuum conditions are created in the chamber using vacuum pump 19 to evacuate an effective amount of air initially contained in the chamber. Air can be detrimental to the oxygen implantation step in that it reduces the efficiency of the energy beam's effect on the particle. Evacuating an effective 30 amount of air is intended to mean that enough air is removed so that the energy beam has the

ability to enhance the adsorbent and/or catalytic properties and/or produce catalytic properties in the particle. Typically, vacuum pump 19 is used to evacuate as much air as possible from chamber 11 to maximize the energy beam's efficiency and to allow a beam of lower energy to be used. In one embodiment, the vacuum pressure is from 0.1 to 5 millitorr, preferably from 1 to 2.5 millitorr. The evacuation time is typically from 1 seconds to 4 hours, preferably 30
5 seconds to 5 minutes. The chamber is brought up to a pressure of at least atmospheric pressure using an inert gas from cylinder 13 through a high pressure injector 17. In one embodiment, the gauge pressure (pressure above atmospheric) is from 1 to 5,000 psi. Typically, the gauge pressure can be at least about 20 psi to prevent arcing.

10 The inert gas is typically any gas that is inert to chemically reacting with and degrading the adsorbent and/or catalyst particle, and yet, does not impede the energy beam's effectiveness in implanting the oxygen. Typical inert gases include the noble gases, such as helium, neon, argon, krypton, xenon, and radon.

15 The energy source is targeted at the particle contained in the chamber through an energy injector 15 located at the end of the energy source 14. The energy source can be of high enough energy that can force oxygen into the particle and/or add excess charge to the particle. Typically, the energy source is an ion machine which concentrates an ion or electron beam, such as a broad beam ion source or a wide beam photoionizer. The energy source (ion
20 beam or electron beam) can have an energy range of preferably from 1 to 100 eV, more preferably from 10 to 50 eV, even more preferably 15 to 20 eV. In a specific embodiment, the energy source can be a broad beam ion source, manufactured by Commonwealth Scientific Corp., Alexandria, Virginia, U.S.A. This is described in the publication, Kaufman *et al.*, "Characteristics, Capabilities, and Applications of Broad-Beam Sources," Commonwealth
25 Scientific Corporation, Alexandria VA, USA, 1987, which is herein incorporated by reference for all of its teachings and specifically for a description of the broad beam ion source. The energy source 14, utilizes a power supply 21. In a specific embodiment, the power supply can be a Commonwealth IBS-250 high voltage power supply rated up to 1500V with remote operation capabilities. Additionally, the energy beam causes the inert gas to become ionized.

30 The charge introduced into the chamber is at a level sufficient to enhance the adsorbent and/or

catalytic properties of the particle and/or produce catalytic properties in the particle. In one embodiment, an electron beam of 15 to 20 eV was used, although a smaller or larger amount of energy can be used. Once the proper charge has been attained for a sufficient time, the energy source is turned off. This sufficient time can be very short, on the order of less than a second to about 10 seconds, although a longer time is not detrimental. Then, the chamber pressure is reduced via a release valve 16.

The present invention should be distinguished from the use of different, particularly higher, energy levels of the ion or electron beam. As described above, the penetration of ions and other substituents underneath the surface of the particle is typically achieved at energy levels ranging from from 1 to 100 eV. If the energy level is raised, other manipulations outside the scope of this invention are performed. For example, in ion-beam etching, the beam is directed toward a surface, with the objective of removing material from that surface. Etching is also referred to as physical sputtering, a term that is known to one skilled in the art. The maximum removal of material by physical sputtering is usually obtained in the energy range of 300-500 eV. The present invention should also be distinguished over uses of different types of energy sources or the non-targeting of the particle by the energy source, such as particularly gamma radiation, x-rays, electromagnetic radiation, electric fields, and lasers, and non-targeted plasma fields.

Not wishing to be bound by theory, it is theorized that the energy beam causes oxygen, believed to be atomic and/or diatomic oxygen, present on the surface of the particle to be pushed below the surface of the particle, which then becomes tightly bound to the internal structure of the particle. In particular, ions of the inert gas generated by the ion or electron beam collide against the particle, and it is the momentum of these ions that force oxygen to penetrate the surface of the particle. For crystalline particles, the oxygen becomes tightly bound within the crystal lattice. The atomic and/or diatomic oxygen originates from oxygen that is on the outer surface of the crystal lattice of the particle or from residual water or air on the surface of the particle. This increases the adsorbent and/or catalytic characteristics of the particle and can create catalytic properties, including room temperature catalytic capabilities, in the particle. The process creates a more active surface by creating surface defects. Surface

defects have long been proposed as the active sites in many catalytic reactions.

In another embodiment, in the energy beam process above, after the air has been removed from the chamber, inert gas is added so that the chamber pressure is brought up to a high pressure. Typically, the gauge pressure can be from about at least 100 psi, more preferably at least 1,000 psi, even more preferably at least 5,000 psi. Even higher pressures can be used if the chamber 15 is of a high enough pressure rating. The high pressure or compression is maintained for a sufficient time to increase the density of the particle. Typically, about ten minutes of high pressure is sufficient. After the energy source has been introduced for a sufficient time in the chamber as described above, the energy source is turned off and then the chamber pressure is rapidly lowered via release valve 16. By rapidly, it is preferably meant about 3 seconds. This increases the surface area of the particle.

Not wishing to be bound by theory, it is theorized that as the pressure from the chamber is rapidly released, the contents of the chamber expand simultaneously but at different rates of expansion. The charged inert gas expands at a much faster rate than that of the particulate matter due to the density differences between the two substances. Due to this expansion rate difference, the charged inert gas travels rapidly and penetrates or explodes into and through the particles or inert gas that is trapped within the particle rapidly escapes. This rapid penetration or escape alters the pore structure and increases the amount of pores of the particle. The surface area of the particle is thereby greatly increased, increasing the overall adsorption capability of the particle. Depending on the particle employed, the BET surface area can be increased at least 1%, more preferably at least 5%, even more preferably at least 10%, even more preferably at least 20%, even more preferably at least 30%. The lower density particles, such as activated carbon, can achieve a greater increase in surface area.

The chamber pressure and the energy level can be varied to produce different effects to meet the particular physical and chemical requirements for the specific particle end use. Varying the pressure and energy level parameters can alter the ability of the particle to adsorb or degrade a particular contaminant.

In another embodiment of this invention, the surface area enhancement aspect of the process can be practiced alone without the energy beam aspect. In this embodiment, the inert gas only needs to be inert to the particle and does not have to be inert to the effects of the energy beam. Thus, gases such as air and CO₂ can also be used in the this embodiment.

5 In another embodiment, the energy beam aspect can be practiced alone without the surface area enhancement aspect. In this embodiment, the energy beam is targeted directly at the particle to implant oxygen within the particle. This can be done in the batch process described above or a semi-batch or continuous process. In a semi-batch process, particles are automatically moved into the chamber where they are treated and automatically removed from
10 the chamber. In a continuous process, in one embodiment, the particles are provided on a conveyor belt system. Air is displaced from the area around the particles by inert gas to provide a viable path for the energy beam, which is set up along side or overhead of the conveyor belt system. The energy beam is either continuously on or is turned on as the particles reach a specific point along the conveyer belt system. In a variation of the
15 embodiments of this invention, the air removal and replacement with inert gas steps in the batch or semi-batch processes and the air displacement by inert gas step in the continuous process can be avoided by using a high or extremely high level of output energy source, such that, the air does not impede the oxygen from penetrating the surface of the particle while maintaining a low enough energy on the particle, such as from 1 to 100 eV, so that etching
20 and sputtering does not occur. In another embodiment of a continuous process, the particles are filtered through a mesh screen sieve, which has been substantially ionized to cause the oxygen on the particle to penetrate the particle.

The particles of this invention are characterized by having an increased level of oxygen
25 at least on the surface of the particle. This increased level of oxygen is higher than the total of the stoichiometric amount of oxygen expected in the particle and that found as residual oxygen on the surface of the particle. The oxygen implanted particle has at least 1.1 times the oxygen atom per cent to non-oxygen atom per cent ratio at its surface compared to the initial non-oxygen implanted particle, wherein the surface characterization is determined by an x-ray
30 photoelectron spectroscopy (XPS or ESCA) spectrometer, a device well known to those of

skill in the art. Even more preferably, the particle has at least a 1.5 fold increase in oxygen ratio, even more preferably the particle has at least a 2 fold increase in oxygen ratio, even more preferably, at least a 4 fold increase in oxygen ratio, even more preferably at least a 6 fold increase in oxygen ratio.

5 The particle of this invention can be used in any adsorption and/or catalytic application known to those of ordinary skill in the art to achieve superior results over prior art particles. Additionally, the particle of the invention can be used in various adsorption and/or catalytic applications never before contemplated in the art. In one embodiment, the particle is used for environmental remediation applications. In this embodiment, the particle can be used to
10 remove contaminants, such as heavy metals, organic compounds, including for example but not limited to, chlorinated organic compounds and volatile organic compounds, inorganic compounds, or mixtures thereof. Specific examples of contaminants include, but are not limited to, acetone, microbials, ammonia, benzene, carbon monoxide, chlorine, dioxane, ethanol, ethylene, formaldehyde, hydrogen cyanide, hydrogen sulfide, methanol,
15 trichloroethylene, methyl ethyl ketone, methylene chloride, nitrogen oxides, propylene, styrene, sulfur dioxide, toluene, vinyl chloride, arsenic, lead, iron, phosphates, selenium, cadmium, uranium, plutonium, radon, 1,2-dibromo-3-chloropropane (DBCP), chromium, tobacco smoke, and cooking fumes. The particle of this invention can remediate individual contaminants or multiple contaminants from a single source.

20 For environmental remediation applications, typically, particles of the invention are placed in a container, such as a filtration unit. The contaminated stream enters the container at one end, contacts the particles within the container, and the purified stream exits through another end of the container. The flow rate of the contaminant stream and the amount of
25 particle material needed can be determined by one of skill in the art with routine experimentation by determining the capacity needed. The particles contact the contaminants within the stream and bond to and remove the contamination from the stream. The particles can also eliminate certain contaminants by catalyzing the conversion of the contaminants into other components. Typically, in the adsorption application, the particles become saturated
30 with contaminants over a period of time, and the particles must be removed from the container

and replaced with fresh particles. The contaminant stream can be a gas, such as air, or liquid, such as water.

The particle of this invention bonds with the contaminant so that the particle and contaminant are tightly bound. This bonding makes it difficult to remove the contaminant from the particle, allowing the waste product to be disposed of into any public landfill. Measurements of contaminants adsorbed on the particles of this invention using a Toxicity Characteristic Leachability Procedure (TCLP) test known to those of skill in the art showed that there was a very strong interaction between the particles of this invention and the contaminants such that the contaminant can be held very tightly.

The particles of this invention have superior ability to adsorb contaminants due to enhanced physical and chemical properties of the particle. The particles of this invention can adsorb a larger amount of adsorbate per unit volume or weight of adsorbent particles than a non-enhanced particle. The particle of this invention surprisingly removes contaminants in various streams at both high and low concentrations of contaminants. Also, the particles of this invention can reduce the concentration of contaminants or adsorbate material in a stream to a lower absolute value than is possible with a non-enhanced particle. In particular embodiments, the particles of this invention can reduce the contaminant concentration in a stream to below detectable levels, believed to be never before achievable with prior art particles.

The particles of this invention can also have a newly added catalytic property. Specifically, the increased oxygen content in the particle matrix allows the particle to act as a catalyst. For example, the particle has the ability to catalyze the break down of organics, such as hydrocarbon compounds or substituted hydrocarbons and has the ability to catalyze the conversion of CO, SO_x, or NO_x into other components, even at low heat or room temperatures.

Particular end uses contemplated for this invention include, but are not limited to, reducing or eliminating contaminants for particular applications, such as waste water treatment

facilities, sewage facilities, municipal water purification facilities, in-home water purification systems, smoke stack effluents, vehicle exhaust effluents, engine or motor effluents, home or building air purification systems, home radon remediations, landfill leachates, manufacturing facility chemical waste effluents, and the like.

5 Prior art adsorbents, such as activated carbon, when sprayed with anti-microbials, tend to lose their adsorbent properties. Conversely, the increased adsorbent properties allow the particles of the present invention to be sprayed with anti-microbials while still retaining the particle's adsorbent properties.

10 A preferred binder that can be used with the particles of this invention is a colloidal metal oxide or colloidal metalloid oxide binder as disclosed in applicants copending application filed on the same date as this application and entitled "Adsorbent and/or Catalyst and Binder System and Method of Making and Using Therefor," which is (1) a continuation-in-part of PCT/US96/05303, filed April 17, 1996, pending, which is a continuation-in-part of U.S.
15 application serial No. 08/426,981, filed April 21, 1995, pending; (2) a continuation-in-part of U.S. application serial No. 08/426,981, filed April 21, 1995, pending; (3) a continuation-in-part of U.S. application serial No. 08/662,331, filed June 12, 1996, pending, which is a continuation-in-part of PCT/US95/15829, filed June 12, 1995, pending, which is a continuation-in-part of U.S. application serial No. 08/351,600, filed December 7, 1994,
20 abandoned; and (4) a continuation-in-part of PCT/US95/15829, filed June 12, 1995, pending, which is a continuation-in-part of U.S. application serial No. 08/351,600, filed December 7, 1994, abandoned. All of the above applications are hereby incorporated by this reference in their entireties for all of their teachings. Additionally, this binder can be used with an untreated (non-ion or electron beam enhanced) particle of this invention and/or a treated
25 particle of this invention. This binder can be used on any of the particle compositions referred to above or below of this invention, whether ion or electron beam enhanced or not.

 These various embodiments of the invention are described in the copending application filed on even date as follows.

In accordance with the purpose(s) of this invention, as embodied and broadly described herein, this invention, in one aspect, relates to a method for producing an adsorbent and/or catalyst and binder system comprising

- i) mixing components comprising
 - a) a binder comprising a colloidal metal oxide or colloidal metalloid oxide,
 - b) an oxide adsorbent and/or catalyst particle, and
 - c) an acid,
- ii) removing a sufficient amount of water from the mixture to cross-link components a and b to form an adsorbent and/or catalyst and binder system.

In another aspect, the invention provides for an adsorbent and/or catalyst system made by the processes of the invention.

In one aspect, the invention provides an adsorbent and/or catalyst and binder system comprising a binder that has been cross-linked with at least one type of oxide adsorbent and/or catalyst particle.

In yet another aspect, the invention provides a method for reducing or eliminating the amount of a contaminant from a liquid or gas stream comprising contacting the adsorbent and/or catalyst binder system with the contaminant in the stream for a sufficient time to reduce or eliminate the amount of contaminant from the stream.

In yet another aspect, the invention provides a method for catalyzing the degradation of an organic compound comprising contacting the organic compound with the adsorbent and/or catalyst system for a sufficient time to catalyze the degradation of an organic compound.

In yet another aspect, the invention provides a method for reducing or eliminating the amount of a contaminant from a gas stream by catalysis comprising contacting the adsorbent and/or catalyst binder system with a gas stream containing a contaminant comprising an oxide of nitrogen, an oxide of sulfur, carbon monoxide, hydrogen sulfide, or mixtures thereof for a

sufficient time to reduce or eliminate the contaminant amount.

In yet another aspect, the invention provides a method for producing an adsorbent and/or catalyst and binder system comprising

- i) mixing components comprising
 - 5 a) a binder comprising a colloidal metal oxide or colloidal metalloid oxide,
 - b) a first adsorbent and/or catalyst particle that does not cross-link with the binder, and
 - c) an acid,
- 10 ii) removing a sufficient amount of water from the mixture to cross-link component a to itself, thereby entrapping and holding component b within the cross-linked binder, to form an adsorbent and/or catalyst and binder system.

In another aspect the invention relates to a composition for binding adsorbent and/or catalytic particles to produce an agglomerated particle comprising (a) a colloidal metal
15 oxide or colloidal metalloid oxide and (b) an acid.

In another aspect the invention relates to a kit for binding adsorbent and/or catalytic particles to produce an agglomerated particle comprising (a) a colloidal metal oxide or colloidal metalloid oxide and (b) an acid.

20

In yet another aspect, the invention provides a method for binding adsorbent and/or catalytic particles, comprising the steps of:

- (a) mixing colloidal alumina or colloidal silica with the particles and an acid;
- (b) agitating the mixture to homogeneity; and
- 25 (c) heating the mixture for a sufficient time to cause cross-linking of the aluminum oxide in the mixture.

When the system acts as an adsorbent, the adsorbent and binder system of this invention has improved or enhanced adsorptive features. In one embodiment, the system of
30 this invention can adsorb a larger amount of adsorbate per unit volume or weight of adsorbent

particles than a prior art system. In another embodiment, the adsorbent and binder system of this invention can reduce the concentration of contaminants or adsorbate material in a stream to a lower absolute value than is possible with a non-bound or prior art-bound particle. In particular embodiments, the adsorbent and binder system of this invention can reduce the contaminant concentration in a stream to below detectable levels. Adsorption is a term well known in the art and should be distinguished from absorption. The adsorbent particles of this invention chemically bond to and very tightly retain the adsorbate material. These chemical bonds are ionic and/or covalent in nature.

The catalyst and binder system of the invention can also be used for the catalytic decomposition or remediation of contaminants. The catalyst system achieves improved catalytic performance or catalytic properties never seen before for a particular contaminant. The adsorbent and/or catalyst and binder system can be prepared by techniques set forth below to form a multifunctional composite particle. The catalysis can be at room temperature for certain applications.

The binder comprises an oxide particle that can react, preferably cross-link, with the other oxide complexes. This binder can also react, preferably cross-link, with itself. The binder forms cross-links with other oxide complexes upon drying by forming chemical bonds with itself and with other oxides. Under acidic conditions, the binder has a large number of surface hydroxyl groups. In one embodiment, the binder, which is designated as B-OH, cross-links with itself upon the loss of water to generate B-O-B. In addition cross-linking with itself, the binder B-OH can also cross-link with an adsorbent and/or catalyst oxide complex (M-O) or hydroxyl complex (M-OH) to produce B-O-M. The resulting binder system consists of a three dimensional network or matrix wherein the component particles are bound together with B-O-B and B-O-M bonds. The resulting system can be used as an adsorbent and/or catalyst system. The resultant system is sometimes referred to as an agglomerated particle.

"Colloidal metal or metalloid oxide (i.e. colloidal metal oxide or colloidal metalloid oxide) binder" as defined herein means a particle comprising a metal or metalloid mixed hydroxide, hydroxide oxide or oxide particle, such that the weight loss from the colloidal

metal or metalloid oxide binder due to loss of water upon ignition is from 1 to 100%, 5 to 99%, 10 to 98%, or 50 to 95% of the theoretical water weight loss on going from the pure metal or metalloid hydroxide to the corresponding pure metal or metalloid oxide. The loss of water on going from the pure metal or metalloid hydroxide to the corresponding pure metal or metalloid oxide (e.g. the conversion of $n M(OH)_x$ to M_nO_m and $y H_2O$ or more specifically from $2 Al(OH)_3$ to Al_2O_3 and $3 H_2O$) is defined as 100% of the water weight loss. Thus, the weight loss refers to loss of water based on the initial weight of water (not the total initial binder weight). There is a continuum of metal or metalloid hydroxides, hydroxide oxides, and oxides in a typical commercial product, such that, loss or removal of water from the metal or metalloid hydroxides produces the corresponding hydroxide oxides which upon further loss or removal of water give the corresponding metal or metalloid oxides. Through this continuum the loss or removal of water produces M-O-M bonds, where M is a metal or metalloid. The particles of this continuum, except for the pure metal or metalloid oxides, are suitable to serve as colloidal metal or colloidal oxide binders in this invention.

In another embodiment, the binder system involves the use of a binder in combination with a particle with few or no surface hydroxyl groups, such that the particle does not cross-link or only nominally cross-links with the binder. Examples of particles that possess only nominal amounts or that do not possess surface hydroxyl groups include particles of metals, such as, but not limited to tin or zinc, or carbon. In another embodiment, component b does not contain an oxide particle. Metal alloys such as bronze can also be used. In a preferred embodiment, the particle is activated carbon. In this embodiment, the binder cross-links with itself in a manner described above to form a three dimensional network or matrix that physically entraps or holds component b without cross-linking or cross-linking only to a very small degree with component b. The resulting binder system can be used as an adsorbent and/or catalyst system.

In another embodiment, the invention is directed to a method for producing an adsorbent and/or catalyst and binder system comprising

i) mixing components comprising

a) a binder comprising a colloidal metal oxide or colloidal metalloid oxide,

- b) a first adsorbent and/or catalyst particle that does not cross-link with the binder, and
- c) an acid,

5 ii) removing a sufficient amount of water from the mixture to cross-link component a to itself, thereby entrapping and holding component b within the cross-linked binder, to form an adsorbent and/or catalyst and binder system, further comprising a second adsorbent and/or catalyst particle that cross-links with the binder, thereby cross-linking the binder and the second particle and thereby entrapping and holding the first particle within the cross-linked binder and/or within the cross-linked binder and second particle. In this embodiment, the system comprises a binder and oxide adsorbent and/or catalyst particles that cross-links with the binder as well as particles that have a limited amount of surface hydroxyl groups, which do not cross-link with the binder. In this case, the binder cross links to itself and to the oxide complex particles, and the binder also forms a network or matrix around the particles that have a limited number of surface hydroxyl groups.

15 Binders that can be used in the present invention are colloidal metal or metalloid oxide complexes. Colloidal as used herein is defined as an oxide group that has a substantial number of hydroxyl groups that can form a dispersion in aqueous media. This is to be distinguished from the other use of the term colloid as used in regard to a size of less than 1 μm . The binders herein are typically small in size, *e.g.* less than 150 μm , but they do not have to be all less than 1 μm . Typically, the binder is un-calcined to maximize the hydroxyl group availability. Moreover, they must have a substantial number of hydroxyl groups that can form a dispersion in aqueous media, which is not always true of colloid particles merely defined as being less than 1 μm . Examples of binders include but are not limited to any metal or metalloid oxide complex that has a substantial number of hydroxyl groups that can form a dispersion in aqueous media. In one embodiment, the binder is colloidal alumina, colloidal silica, colloidal metal oxide where the metal is iron, or a mixture thereof, preferably colloidal alumina or colloidal silica. Colloidal alumina can be a powder, sol, gel or aqueous dispersion. Colloidal alumina may be further stabilized with an acid, preferably nitric acid, and even more preferably 3 to 4% nitric acid. In a preferred embodiment, the colloidal alumina is un-calcined with a sufficient number of hydroxyl groups such that the total particle weight loss (as

20

25

30

distinguished from just water weight loss discussed above) upon ignition is between from 5% to 34%, more preferably from 20% to 31%. The colloidal alumina size is preferably from 5 nm to 400 μm , preferably at least 30 wt% is less than 25 μm and 95 wt% is less than 100 μm . The colloidal silica is preferably un-calcined with a sufficient number of hydroxyl groups such that the total particle weight loss upon ignition is between from 5% to 37%, more preferably from 20% to 31%. The colloidal silica size is preferably from 5 nm to 250 μm , preferably at least 30 wt% is less than 25 μm and 95 wt% is less than 100 μm . In one embodiment, the binder is from 1% to 99.9% by weight of the mixture, preferably from 10% to 35% by weight. As used herein, the binder will be referred to as "colloidal" to distinguish it from particle b, as the composition types can be the same, *e.g.* both can contain aluminum oxides.

Although prior art binders can be used in combination with the binder system of the present invention, these prior art binders lack certain advantages. In the present invention, the activity is not degraded when exposed to aqueous solutions. The system is also very durable and not subject to falling apart when exposed to a waste stream, unlike other prior art adsorbent and/or catalyst and binder systems, such as polyvinyl pyrrolidone, starch, or cellulose.

The invention contemplates the use of any prior art oxide adsorbent and/or catalyst particle or composite particle of two or more types of particles and binder system, but replacing the prior art binder with the binder of the present invention. In one aspect, the invention provides an adsorbent and/or catalyst and binder system comprising a binder that has been cross-linked with at least one type of oxide adsorbent and/or catalyst particles. In one embodiment, component b comprises at least two different types of oxide adsorbent and/or catalyst particles, to form a cross-linking between the binder and both particles to thereby form a composite particle.. In another embodiment, component b comprises at least three different types of adsorbent and/or catalyst particles. In a preferred embodiment, component b comprises an oxide particle, preferably a metal oxide particle, and even more preferably a non-ceramic, porous metal oxide particle. Examples of such particles include, but are not limited to, oxide complexes, such as transition metal oxides, lanthanide oxides, thorium oxide, as well as oxides of Group IIA (Mg, Ca, Sr, Ba), Group IIIA (B, Al, Ga, In, Tl), Group IVA (Si, Ge,

Sn, Pb), and Group VA (As, Sb, Bi). In general, any oxide complex that is a basic anhydride is suitable for component b. In another embodiment, component b comprises an oxide of aluminum, titanium, copper, vanadium, silicon, manganese, iron, zinc, zirconium, tungsten, rhenium, arsenic, magnesium, thorium, silver, cadmium, tin, lead, antimony, ruthenium, osmium, cobalt or nickel or zeolite. Typically, any oxidation state of the oxide complexes may be useful for the present invention. The oxide can be a mixture of at least two metal oxide particles having the same metal with varying stoichiometry and oxidation states. In one embodiment, component b comprises Al_2O_3 , TiO_2 , CuO , Cu_2O , V_2O_5 , SiO_2 , MnO_2 , Mn_2O_3 , Mn_3O_4 , ZnO , WO_2 , WO_3 , Re_2O_7 , As_2O_3 , As_2O_5 , MgO , ThO_2 , Ag_2O , AgO , CdO , SnO_2 , PbO , FeO , Fe_2O_3 , Fe_3O_4 , Ru_2O_3 , RuO , OsO_4 , Sb_2O_3 , CoO , Co_2O_3 , NiO or zeolite. In a further embodiment, component b further comprises a second type of adsorbent and/or catalyst particles of an oxide of aluminum, titanium, copper, vanadium, silicon, manganese, iron, zinc, zirconium, tungsten, rhenium, arsenic, magnesium, thorium, silver, cadmium, tin, lead, antimony, ruthenium, osmium, cobalt or nickel or zeolite, activated carbon, including coal and coconut carbon, peat, zinc or tin. In another embodiment, component b further comprises a second type of adsorbent and/or catalyst particles of aluminum oxide, titanium dioxide, copper oxide, vanadium pentoxide, silicon dioxide, manganese dioxide, iron oxide, zinc oxide, zeolite, activated carbon, peat, zinc or tin particle. Typical zeolites used in the present invention include "Y" type, "beta" type, mordenite, and ZSM5. In a preferred embodiment, component b comprises non-amorphous, non-ceramic, crystalline, porous, calcined aluminum oxide that was produced by calcining the precursor to the calcined aluminum oxide at a particle temperature of from 400°C to 700°C , preferably in the gamma, chi-rho, or eta form. The precursor to calcined aluminum oxide can include but is not limited to boehmite, bauxite, pseudo-boehmite, scale, $\text{Al}(\text{OH})_3$, and alumina hydrates. In the case of other metal oxide complexes, these complexes can also be calcined or uncalcined.

The adsorbent and/or catalyst particles used in this invention can be unenhanced or enhanced by processes known in the art or described below. For example, the particles can be dried to be activated or can be of a composition or treated by ion or electron beam or acid

activation or enhancement treatment processes disclosed in the prior filed parent applications of and in applicants' two copending applications filed on the same date as this application and entitled (1) "Enhanced Adsorbent and Room Temperature Catalyst Particle and Method of Making and Using Therefor," which is a continuation-in-part of PCT/US96/05303, filed April 17, 1996, pending, which is a continuation-in-part of U.S. application serial No. 08/426,981, filed April 21, 1995, pending, and (2) "Acid Contacted Enhanced Adsorbent Particle and Method of Making and Using Therefor," which is a continuation-in-part of U.S. application serial No. 08/662,331, filed June 12, 1996, pending, which is a continuation-in-part of PCT/US95/15829, filed June 12, 1995, pending, which is a continuation-in-part of U.S. application serial No. 08/351,600, filed December 7, 1994, abandoned, the disclosures of both applications filed on the same date as this application and all of their prior filed priority applications are herein incorporated by this reference in their entireties for all of their teachings, indirectly, but not limited to particle compositions and methods of treatment.

An acid is required to cross-link the binder with component b. The addition of an acid to the binder facilitates or enables the reaction between the binder and the oxide particle. A strong or dilute acid can be used. A dilute acid is preferred to minimize etching of certain particles. Typically the acid is diluted with water to prevent dissolution of the particle and for cost effectiveness. The acid treatment is preferably of a concentration (*i.e.* acid strength as measured by, *e.g.*, normality or pH), acid type, temperature and length of time to cross-link the binder and component b.

In one embodiment, the acid comprises nitric acid, sulfuric acid, hydrochloric acid, boric acid, acetic acid, formic acid, phosphoric acid or mixtures thereof, preferably acetic acid or nitric acid. In another embodiment, the concentration of the acid is from 0.15 N to 8.5 N, preferably from 0.5 N to 1.7 N. The volume of dilute acid used must be high enough so that the adsorbent and/or catalyst particle of the present invention can be used as is or further processed, such as extruded or filter pressed.

In order to ensure efficient cross-linking between the binder and the oxide particle component, water is removed from the resulting binder system. This is typically performed by

using a drying agent or heating the system. The cross-linking temperature as used herein is the temperature at which cross-linking between the binder and the oxide adsorbent and/or catalyst component b occurs at an acceptable rate or the temperature at which the binder reacts with itself at an acceptable rate. In one embodiment, the cross-linking temperature is from 25°C to 400°C. Thus, in one embodiment, the cross-linking temperature for certain binders is at room temperature although the rate of cross-linking at this temperature is slow. In a various
5 embodiments, the cross-linking temperature is from 50°C, 70°C, 110°C, or 150°C to 200°C, 250°C, 300°C, or 350°C, preferably 150°C to 300°C, even more preferably about 250°C. The cross-linking process can take place in open air, under an inert atmosphere or under reduced pressure. The cross-linking temperature can effect the activity of the adsorbent
10 and/or catalyst and binder system. When cross-linking occurs in the open air, then the particle is more susceptible to oxidation as the cross-linking temperature is increased. Oxidation of the particle can ultimately reduce the activity of the particle.

Preferably, during or after step (i), the mixture of step (i) is not heated above the cross-
15 linking temperature of the colloidal metal oxide or colloidal metalloid oxide. Preferably, during or after step (i), the mixture of step (i) is not heated to or above the calcining temperature of the colloidal metal oxide or colloidal metalloid oxide. Preferably, during or after step (i), the mixture of step (i) is not heated to or above the calcining temperature of the particle. In various embodiments, during or after step (i), the mixture of step (i) is not heated
20 above 500° C, 450° C, 400° C, 350° C, 300° C, or 250° C, preferably not above 400°C. Cross-linking should be distinguished from calcining. Calcining typically involves heating a particle to remove any residual water that may be on the particle as well as change the lattice structure of the particle to form a crystalline particle. For example for producing a crystalline aluminum oxide particle, the calcining temperature is about 400°C to about 700°C.
25 Calcining also removes the hydroxyl groups on the binder that are required for cross-linking. Therefore, heating the system during or after step (i) above the cross-linking temperature into the particle or binder calcining temperature range or above is detrimental to the system. Thus, prior art systems, where mixtures of colloidal alumina and/or colloidal silica are (1) calcined or recalcined or (2) heated to form a refractory material are not a part of this invention.

In another aspect, the invention provides for an adsorbent and/or catalyst system made by the process of the invention.

The binder system of the invention is made in one embodiment by the following general process. The (1) binder and (2) adsorbent and/or catalyst particles are pre-mixed in dry form. The colloidal binder can be added or prepared *in situ*. For example, alum could be added as a dry powder and converted to colloidal alumina in situ. Other aluminum based compounds can be used for the in situ process, such as aluminum chloride, aluminum secondary butoxide, and the like. A solution of the acid is added to the mixture, and the mixture is stirred or agitated, typically from 1 minute to 2 hours, preferably from 10 minutes to 40 minutes, until the material has a homogeneous "clay" like texture. The mixture is then ready for cross-linking or can be first fed through an extruder and then cut or chopped into a final shape, preferably spheres, pellets or saddles, typically of a size from 0.2 mm to 3 mm, preferably 0.5 to 1.5 mm. After the final shape is made, the product is transferred to a drying oven where they are dried from 15 minutes to 4 hours, preferably from 30 minutes to 2 hours. Once the binder is added to the adsorbent and/or catalyst particles (component b), the mixture is not heated to calcine or recalcine the particle b or binder. Such calcining or recalcining would detrimentally change the surface characteristics of component b by closing up the micropores. Additionally, the particles of the invention are preferably not sintered, as this would detrimentally affect the micropores by closing up the micropores and would detrimentally decrease the pore volume and surface area. The particles and binder system are also not heated above the calcining temperature to form a refractory material. Any other process that would increase the size or eliminate micropores, enlarge the size of, create macropores at the expense of micropores or destroy macropores, or would decrease the surface area available for adsorption or catalysis should preferably be avoided.

The size and shape of the particles used in this invention prior to extruding can vary greatly depending on the end use. Typically, for adsorption or catalytic applications, a small particle size such as 5 μm or greater to about 250 μm are preferable because they provide a larger surface area than large particles.

In yet another aspect, the invention provides a method for reducing or eliminating the amount of a contaminant from a liquid or gas stream comprising contacting the adsorbent and/or catalyst binder system with the contaminant in the stream for a sufficient time to reduce or eliminate the amount of contaminant from the stream. In one embodiment, the stream is a liquid, preferably water. In another embodiment, the stream is a gas, preferably comprising air or natural gas.

The adsorbent and/or catalyst binder system of this invention can be used for environmental remediation applications. In this embodiment, contaminants from a liquid or gas stream can be reduced or eliminated by a catalysis reaction. In another embodiment, contaminants from a liquid or gas stream can be reduced or eliminated by an adsorption reaction. The particle can be used to remove contaminants, such as, but not limited to, heavy metals, organics, including hydrocarbons, chlorinated organics, including chlorinated hydrocarbons, inorganics, or mixtures thereof. Specific examples of contaminants include, but are not limited to, acetone, ammonia, benzene, carbon monoxide, chlorine, hydrogen sulfide, trichloroethylene, 1,4-dioxane, ethanol, ethylene, formaldehyde, hydrogen cyanide, hydrogen sulfide, methanol, methyl ethyl ketone, methylene chloride, oxides of nitrogen such as nitrogen oxide, propylene, styrene, oxides of sulfur such as sulfur dioxide, toluene, vinyl chloride, arsenic, cadmium, chlorine, 1,2-dibromochloropropane (DBCP), iron, lead, phosphate, radon, selenium, or uranium. The adsorbent and/or catalyst binder system of this invention can remediate individual contaminants or multiple contaminants from a single source. This invention achieves improved efficiency by adsorbing a higher amount of contaminants and by reducing the contamination level to a much lower value than by non-enhanced particles.

In yet another aspect, the invention provides a method for catalyzing the degradation of an organic compound comprising contacting the organic compound with the adsorbent and/or catalyst system for a sufficient time to catalyze the degradation of an organic compound. In one embodiment, the catalysis reaction is at room temperature. In a one embodiment, the organic compound is a chlorinated organic compound, such as trichloroethylene (TCE). In one embodiment, the catalyst and binder system catalyzes the

hydrolysis of the chlorinated organic compounds.

In yet another aspect, the invention provides a method for reducing or eliminating the amount of a contaminant from a gas stream by catalysis comprising contacting the adsorbent and/or catalyst binder system with a gas stream containing a contaminant comprising an oxide
5 of nitrogen, an oxide of sulfur, carbon monoxide, hydrogen sulfide, or mixtures thereof for a sufficient time to reduce or eliminate the contaminant amount. In one embodiment, the catalysis reaction is at room temperature.

For environmental remediation applications, adsorbent and/or catalyst particles of the
10 invention are typically placed in a container, such as a filtration unit. The contaminated stream enters the container at one end, contacts the particles within the container, and the purified stream exits through another end of the container. The particles contact the contaminants within the stream and bond to and remove the contamination from the stream. Typically, the particles become saturated with contaminants over a period of time, and the particles must be
15 removed from the container and replaced with fresh particles. The contaminant stream can be a gas stream or liquid stream, such as an aqueous stream. The particles can be used to remediate, for example, waste water, production facility effluent, smoke stack gas, auto exhaust, drinking water, and the like.

20 The particle/binder system of the invention can be used preferably as the adsorbent or catalytic medium itself. In an alternate embodiment, the system is used as an adsorbent or catalytic support.

When the particle adsorbs a contaminant, the particle of this invention bonds with the
25 contaminant so that the particle and contaminant are tightly bound. This bonding makes it difficult to remove the contaminant from the particle, allowing the waste to be disposed of into any public landfill. Measurements of contaminants adsorbed on the particles of this invention using an EPA Toxicity Characteristic Leachability Procedure (TCLP) test known to those of skill in the art showed that there was a very strong interaction between the particles of this
30 invention and the contaminants such that the contaminant is held very tightly.

Although the particle system bonds tightly to the contaminant, the system of the invention can be regenerated by various techniques, such as by roasting it in air to reoxidize the particles.

In one embodiment, component b comprises aluminum oxide, copper oxide, and manganese dioxide. In this embodiment, the binder is preferably colloidal alumina. In this
5 embodiment, the acid is preferably acetic acid. In this embodiment, the binder is from 1 to 99.9 parts by weight, preferably from 5 to 35 parts by weight, the aluminum oxide is from 1 to 99.9 parts by weight, preferably from 55 to 85 parts by weight, the copper oxide is from 1 to 99.9 parts by weight, preferably from 1 to 20 parts by weight, and the manganese oxide is
10 from 1 to 99.9 parts by weight, preferably from 1 to 20 parts by weight. In another embodiment, the binder is 20 parts by weight, aluminum oxide is 70 parts by weight, copper oxide is 5 parts by weight, and manganese dioxide is 5 parts by weight.

In another embodiment, component b comprises aluminum oxide and activated carbon.
15 In this embodiment, the binder is preferably colloidal alumina. In this embodiment, the acid is preferably acetic acid. In this embodiment, the binder is from 1 to 99.9 parts by weight, preferably from 5 to 35 parts by weight, the aluminum oxide is from 1 to 99.9 parts by weight, preferably from 45 to 75 parts by weight, and the activated carbon is from 1 to 99.9 parts by weight, preferably from 35 to 55 parts by weight. In another embodiment, the binder is 20
20 parts by weight, aluminum oxide is 60 parts by weight, and activated carbon is 5 parts by weight.

In another embodiment, component b comprises copper oxide and manganese dioxide. In this embodiment, the binder is preferably colloidal alumina. In this embodiment, the acid is
25 preferably acetic acid. In this embodiment, the binder is from 1 to 99.9 parts by weight, preferably from 5 to 35 parts by weight, the copper oxide is from 1 to 99.9 parts by weight, preferably from 35 to 55 parts by weight, and the manganese dioxide is from 1 to 99.9 parts by weight, preferably from 25 to 55 parts by weight. In another embodiment, the binder is 20 parts by weight, copper oxide is 40 parts by weight, and manganese dioxide is 40 parts by
30 weight.

In another embodiment, component b comprises aluminum oxide, copper oxide, manganese dioxide and activated carbon. In this embodiment, the binder is preferably colloidal alumina. In this embodiment, the acid is preferably acetic acid. In this embodiment, the binder is from 1 to 99.9 parts by weight, preferably from 5 to 35 parts by weight, the aluminum oxide is from 1 to 99.9 parts by weight, preferably from 45 to 75 parts by weight, the copper oxide is from 1 to 99.9 parts by weight, preferably from 1 to 20 parts by weight, the manganese dioxide is from 1 to 99.9 parts by weight, preferably from 1 to 20 parts by weight, and activated carbon is from 1 to 99.9 parts by weight, preferably from 1 to 25 parts by weight. In another embodiment, the binder is 19.9 parts by weight, aluminum oxide is 60 parts by weight, copper oxide is 5.98 parts by weight, manganese dioxide is 4.98 parts by weight, and activated carbon is 9.95 parts by weight.

In another embodiment, the component b comprises aluminum oxide, silicon dioxide and activated carbon. In a further embodiment, the particle comprises 1-99 parts, preferably 5-35 parts, more preferably 20 parts by weight aluminum oxide, 1-99 parts, preferably 5-35 parts, more preferably 20 parts by weight silicon dioxide and 1-99 parts, preferably 25-55 parts, more preferably 40 parts by weight activated carbon. In this embodiment, the binder is preferably colloidal alumina and the acid is preferably acetic acid. The binder is from 1 to 99.9 parts by weight, preferably from 5 to 35 parts by weight

In another embodiment, the catalyst and binder system can be used as an oxidation catalyst. In one embodiment, the system comprises colloidal alumina as a binder, Al_2O_3 , and one or more of the following oxide particles of V_2O_5 , WO_2 , WO_3 , TiO_2 , Re_2O_7 , As_2O_3 , As_2O_5 , OsO_4 , or Sb_2O_3 . In another embodiment, the colloidal alumina is from 10 to 30 parts by weight, Al_2O_3 is from 1 to 90 parts by weight, and V_2O_5 , WO_2 , WO_3 , TiO_2 , Re_2O_7 , As_2O_3 , As_2O_5 , OsO_4 , or Sb_2O_3 are each from 1 to 90 parts by weight.

In another embodiment, the catalyst and binder system can be used as a Lewis acid catalyst. In one embodiment, the system comprises colloidal alumina as a binder, Al_2O_3 , and one or more of the following oxide particles of V_2O_5 , ZrO_2 , TiO_2 , MgO , ThO_2 or lanthanide oxides. In another embodiment, the colloidal alumina is from 10 to 30 parts by weight, Al_2O_3

is from 1 to 90 parts by weight, and V_2O_5 , ZrO_2 , TiO_2 , MgO , ThO_2 or lanthanide oxides are each from 1 to 90 parts by weight.

In another embodiment, the catalyst and binder system can be used as a cracking catalyst. In one embodiment, the system comprises colloidal alumina as a binder, Al_2O_3 , and one or more of the following oxide particles of CuO , ZnO , Ag_2O , AgO , CdO , SnO_2 , PbO , V_2O_5 , ZrO_2 , MgO , ThO_2 or lanthanide oxides. In another embodiment, the colloidal alumina is from 10 to 30 parts by weight, Al_2O_3 is from 1 to 90 parts by weight, and CuO , ZnO , Ag_2O , AgO , CdO , SnO_2 , PbO , V_2O_5 , ZrO_2 , MgO , ThO_2 or lanthanide oxides are each from 1 to 90 parts by weight.

In another embodiment, the catalyst and binder system can be used as a reduction catalyst. In one embodiment, the system comprises colloidal alumina as a binder, Al_2O_3 , and one or more of the following oxide particles of MnO_2 , Fe_2O_3 , Fe_3O_4 , Ru_2O_3 , OsO_4 , CoO , Co_2O_3 , RuO or NiO . In another embodiment, the colloidal alumina is from 10 to 30 parts by weight, Al_2O_3 is from 1 to 90 parts by weight, and MnO_2 , Fe_2O_3 , Fe_3O_4 , Ru_2O_3 , OsO_4 , CoO , Co_2O_3 , RuO or NiO are each from 1 to 90 parts by weight.

In another embodiment, the catalyst and binder system can be used as a coal gasification catalyst. In one embodiment, the system comprises colloidal alumina as a binder, Al_2O_3 , and one or more of the following oxide particles of Fe_2O_3 , Fe_3O_4 , CoO or Co_2O_3 . In another embodiment, the colloidal alumina is from 10 to 30 parts by weight, Al_2O_3 is from 1 to 90 parts by weight, and Fe_2O_3 , Fe_3O_4 , CoO , or Co_2O_3 , are each from 1 to 90 parts by weight.

In another embodiment, the catalyst and binder system can be used as a coal gas reforming catalyst. In one embodiment, the system comprises colloidal alumina as a binder, Al_2O_3 , and one or more of the following oxide particles of Fe_2O_3 , Fe_3O_4 , CoO or Co_2O_3 . In another embodiment, the colloidal alumina is from 10 to 30 parts by weight, Al_2O_3 is from 1 to 90 parts by weight, and Fe_2O_3 , Fe_3O_4 , CoO , or Co_2O_3 , are each from 1 to 90 parts by weight.

In another embodiment, the catalyst and binder system can be used as a hydrogenation

catalyst. In one embodiment, the system comprises colloidal alumina as a binder, Al_2O_3 , and one or more of the following oxide particles of Fe_2O_3 , Fe_3O_4 , CoO or Co_2O_3 . In another embodiment, the colloidal alumina is from 10 to 30 parts by weight, Al_2O_3 is from 1 to 90 parts by weight, and Fe_2O_3 , Fe_3O_4 , CoO or Co_2O_3 are each from 1 to 90 parts by weight.

5 In another embodiment, the catalyst and binder system can be used as a desiccant. In one embodiment, the system comprises colloidal alumina as a binder, Al_2O_3 , and one or more of the following oxide of zeolite, MgO , or ThO_2 . In another embodiment, the colloidal alumina is from 10 to 30 parts by weight, Al_2O_3 is from 1 to 90 parts by weight, and zeolite, MgO , or ThO_2 are each from 1 to 90 parts by weight.

10

In another embodiment, the catalyst and binder system can be used as a catalyst support. In one embodiment, the system comprises colloidal alumina as a binder, Al_2O_3 , and one or more of the following oxide particles of MgO or ThO_2 . In another embodiment, the colloidal alumina is from 10 to 30 parts by weight, Al_2O_3 is from 1 to 90 parts by weight, and MgO or ThO_2 are each from 1 to 90 parts by weight.

15

In another embodiment, the invention relates to a composition for binding adsorbent and/or catalytic particles to produce an agglomerated particle comprising (a) a colloidal metal oxide or colloidal metalloid oxide and (b) an acid. In this composition, in one embodiment, the colloidal metal oxide or colloidal metalloid oxide comprises colloidal alumina or colloidal silica. In this composition, in one embodiment, the acid is acetic acid or nitric acid.

20

In another embodiment, the invention relates to a method for binding adsorbent and/or catalytic particles, comprising the steps of:

25

- (a) mixing colloidal alumina or colloidal silica with the particles and an acid;
- (b) agitating the mixture to homogeneity; and
- (c) heating the mixture for a sufficient time to cause cross-linking of the aluminum oxide in the mixture.

30

In one embodiment, the colloidal alumina or colloidal silica is colloidal alumina. In another embodiment, the colloidal alumina is from 20% to 99% by weight of the mixture. In another

embodiment, the acid is nitric acid.

Experimental

The following examples are put forth so as to provide those of ordinary skill in the art with a complete disclosure and description of how the compounds claimed herein are made and evaluated, and are intended to be purely exemplary of the invention and are not intended to limit the scope of what the inventors regard as their invention. Efforts have been made to ensure accuracy with respect to numbers (e.g., amounts, temperature, etc.) but some errors and deviations should be accounted for. Unless indicated otherwise, parts are parts by weight, temperature is in °C or is at or near room temperature and pressure is at or near atmospheric.

Example 1

Various particles were made in accordance with the procedures of this invention as follows:

i) The procedures used to prepare the particle designated as 1a in Table 1 below, having a composition of 60% Al_2O_3 , 20% carbon, 15% manganese dioxide and 5% copper oxide, is exemplified. The alumina utilized was a gamma calcined (550°C) alumina derived from a high density, low porosity pseudoboehmite alumina or alumina gel. The alumina was pretreated by calcining to 550° C to reach the desired gamma crystalline structure. The carbon utilized in this particle was a coconut based carbon, designated as Polynesian coconut based carbon purchased from Calgon Carbon Corporation. Due to the use of coconut shells in the manufacture of this carbon, there exists a very large surface area as well as micro-pores which are useful for removing contaminants in a gas stream. The four individual particle types were mixed together in their appropriate weight per cents according to the dry weight. They were mixed together into a homogenous dry mixture. A solution of 16% nitric acid was added to the dry particle mixture slowly until the mixture obtained a moist pasty consistency. This consistency allowed the mixture to be extruded into the desired form. The mixture was extruded using a LCI model BTG[®] laboratory extruder. After the mixture was extruded, the extrudate was chopped up into approximately one-sixteenth to one-eighth inch particles and then was dried as described below.

ii) The particles were placed in a vacuum/pressure vessel chamber on an ungrounded target plate. The door to the chamber was secured, and air was pumped out of the chamber down to a pressure of two millitorr. Upon reaching this pressure, argon gas was allowed to bleed into the chamber and reach an internal gauge pressure of about 20 psi. Upon reaching this pressure, the energy beam source was activated to 15 to 20 eV and was applied to the particle on the target area. A Commonwealth Scientific Corp. broad beam ion source was used. Treatment times for the particles vary according to the amount and density of material on the target. For this example, a volume of 50 grams of material was used and a treatment time of ten seconds was used. The treatment times also vary according to the output power from the energy beam source and the internal pressure in the chamber. After ten seconds, the ion source was turned off and the chamber was vented to atmospheric pressure. The sample was then removed from the chamber.

Particles 1b through 1aa were similarly made in accordance with the above-described example for 1a except that the particular compositions were as set forth in Table 1. Also, the carbon utilized for aqueous particle designations 1v and 1w was a coal based carbon. This coal based carbon was purchased from Calgon Carbon Corporation as WHP grade carbon. The particular alumina utilized in particles 1b through 1aa was the same as described above for particle 1a, a gamma calcined alumina. The other components listed below in Table 1 are well known and are readily available to one of skill in the art.

Each of the particle's composition was made in accordance with the procedures of this invention described above. All of the particles in Table 1 that used more than one particle type with the exception of 1v, 1w, and 1aa contained 3% by weight polyvinylpyrrolidinone binder. These particles were dried at 150°C for 30 minutes under reduced pressure. For particles 1v, 1w, and 1aa, 20% by weight colloidal alumina as the binder was used. This 20% of colloidal alumina binder is included in the wt % provided for the aluminum oxide in Table 1 for these particles 1v, 1w, and 1aa, providing 20% colloidal alumina and 20% gamma calcined alumina based on the total composition. These particles were dried at 250°C for 1 hour. The ability of these particles to remediate contaminants was investigated in Examples 2 and 3. The same particle designation system is used in Tables 1-3.

TABLE 1			
PARTICLE DESIGNATION	COMPOSITION ¹ (weight %)	CONTAMINANTS	
		AIRBORNE	AQUEOUS
1a	60% Al ₂ O ₃ , 20% Carbon, 15% MnO ₂ , 5% CuO	Acetone	
1b	100% Al ₂ O ₃	Ammonia	
1c	50% Al ₂ O ₃ , 40% Carbon, 10% SiO ₂	Benzene	
1d	40% Al ₂ O ₃ , 30% V ₂ O ₅ , 20% MnO ₂ , 10% TiO ₂	Carbon Monoxide	
1e	100% Al ₂ O ₃	Chlorine	
1f	100 % Al ₂ O ₃	1,4-Dioxane	
1g	100% Al ₂ O ₃	Ethanol	
1h	100% Al ₂ O ₃	Formaldehyde	
1i	40% Al ₂ O ₃ , 30% MnO ₂ , 20% V ₂ O ₅ , 5% Zeolite, 5% Fe ₂ O ₃	Hydrogen Cyanide	
1j	30% Al ₂ O ₃ , 50% MnO ₂ , 5% Carbon, 5% SiO ₂ , 10% ZnO	Hydrogen Sulfide	
1k	90% Al ₂ O ₃ , 10% Carbon	Methanol	
1l	100% Al ₂ O ₃	Methyl Ethyl Ketone	
1m	40% Al ₂ O ₃ , 20% MnO ₂ , 10% CuO, 30% V ₂ O ₅	Methylene Chloride	
1n	10% Al ₂ O ₃ , 5% CuO, 45% MnO ₂ , 5% zeolite	Nitrogen Oxides	
1o	30% Al ₂ O ₃ , 70% Carbon	Propylene	
1p	30% Al ₂ O ₃ , 70% Carbon	Styrene	
1q	100% Al ₂ O ₃	Sulfur Dioxide	
1r	40% Al ₂ O ₃ , 30% MnO ₂ , 30% Carbon	Toluene	
1s	30% Al ₂ O ₃ , 70% Carbon	Vinyl Chloride	
1t	100% Al ₂ O ₃		Arsenic
1u	100% Al ₂ O ₃		Cadmium
1v	40% Al ₂ O ₃ , 40% Carbon, 20% SiO ₂		Chlorine
1w	40% Al ₂ O ₃ , 40% Carbon, 20% SiO ₂		DBCP

TABLE 1			
PARTICLE DESIGNATION	COMPOSITION ¹ (weight %)	CONTAMINANTS	
		AIRBORNE	AQUEOUS
1x	100% Al ₂ O ₃		Iron
1y	100% Al ₂ O ₃		Lead
1z	100% Al ₂ O ₃		Phosphate
1aa	40% Al ₂ O ₃ , 40% Carbon, 20% SiO ₂		Radon

¹ Activated carbon coconut based was used for the airborne contaminants and for 1aa (radon) and activated carbon coal based was used for aqueous contaminants 1v and 1w.

5

Example 2

The particles made in Example 1 were tested for their ability for removal of various components from air. The tests for the airborne contaminants as summarized in Table 2 below were performed as follows. The contaminant source used was either solvent vapor or an off the shelf bottled gas mixture.

A flow-temperature-humidity control system produced an air stream flowing at 55.5 liters per minute at 25°C and 30% relative humidity. The humidified air was blended with the solvent vapor which was injected into the air stream using a syringe pump. A solvent vaporizer was sometimes used to assist in the evaporation of the solvent at elevated concentrations. The concentration was regulated by the rate of injection. The challenge concentration was measured using an infrared analyzer set at a specific analytical wavelength. The vapor mixture then enters the sample holder. After passing through the sample, the downstream concentration was monitored with another infrared analyzer for the duration of the test.

The gas flow of interest was measured with either a rotameter or a mass flow controller and was blended with a humidified air stream. The mixture then was blended with the humidified air stream. After the influent infrared analysis, the sample entered a sample

holder. The sample holder was a three-inch diameter test vessel, which held a 200 gm amount of particle sample in place using a fritted disk. After passing through the particles, the concentration of the contaminant in the effluent exited the sample holder. The concentration of the contaminant in the effluent side of the particle sample holder was also analyzed with an infrared analyzer. The mixture then passes through the sample. The downstream
5 concentration was measured with either an infared analyzer or an Interscan electrochemical specific gas monitor.

Calibration was conducted on each system component prior to testing. The infared analyzers were calibrated using the static closed loop technique. The electrochemical
10 analyzers were checked using certified gas mixtures. The air flow was checked against a dry gas meter which in turn had been compared to a five cubic foot spirometer. The humudity was checked using the staured salt technique. The temperature probe was compared to a U.S. Bureau of Standards certified mercury in glass thermometer.

15 The test time was ten minutes. Percent removal was calculated as (initial contaminant concentration minus effluent contaminant concentration) divided by initial contaminant concentration. The results are set forth in Table 2 below.

TABLE 2				
PARTICLE DESIGNATION	AIRBORNE CONTAMINANT	INITIAL CONTAMINANT CONCENTRATION (ppm)	PERCENT REMOVAL	FLOW RATE ¹
1a	Acetone	750	100	55.5 l/min.
1b	Ammonia	50	100	55.5 l/min
1c	Benzene	50	100	55.5 l/min.
1d	Carbon Monoxide	10000	100	55.5 l/min
1e	Chlorine	34	100	55.5 l/min
1f	1,4-Dioxane	50	100	55.5 l/min
1g	Ethanol	1000	100	55.5 l/min
1h	Formaldehyde	10	100	55.5 l/min
1i	Hydrogen Cyanide	20	100	55.5 l/min
1j	Hydrogen Sulfide	20	100	55.5 l/min
1k	Methanol	200	100	55.5 l/min
1l	Methyl Ethyl Ketone	1000	100	55.5 l/min
1m	Methylene chloride	50	100	55.5 l/min
1n	Nitrogen Oxides	100	100	55.5 l/min
1o	Propylene	700	100	55.5 l/min
1p	Styrene	50	100	55.5 l/min
1q	Sulfur Dioxide	20	100	55.5 l/min
1r	Toluene	100	100	55.5 l/min
1s	Vinyl Chloride	20	100	55.5 l/min

¹ 40 ft/min velocity, 55.5 l/min volumetric flow.

In Table 2 above, for the formaldehyde test using particle 1h, formaldehyde was not detected on the particle after the test was completed and, as shown in Table 2, no formaldehyde was detected in the effluent stream. This particle 1h acts as a catalyst towards formaldehyde and oxidizes the formaldehyde into what is believed to be CO₂ and water, even at room temperature. This was further evidenced by a separate test in which it was shown that

the formaldehyde was removed from the system over a substantially longer period of time than can be explained if the particle acted only as an adsorbent.

As can also be seen from the above Table 2, carbon monoxide and nitrogen oxides were not detected in the effluent system. It is believed that the CO is converted to CO₂ and water and the NO_x are converted to N₂ and O₂. It is also believed that the remediation of SO₂ was through, at least in part, a catalysis reaction that converted SO₂ into other components. The catalyzed reactions were surprisingly achieved even at room temperature.

Example 3

The particles made in Example 1 were tested for their ability for the removal of various components from water. The test procedures were as follows. For each contaminant run, 5 glass columns of 0.875 inch inner diameter by 12 inches long were prepared, each having a bed volume of test particle of 95 mls. Each bed was flushed with five bed volumes of deionized water by downward pumping at 6 gpm/ft² of cross-sectional flow rate (*i.e.*, about 95 ml/min). Each of the flow rates listed in Table 3 is per foot squared of cross-sectional flow rate. Test solutions for each of the aqueous contaminants were prepared. A total of ten bed volumes, that is, about one liter per column of aqueous contaminant test solution, was pumped through each of the columns. During each run, the aqueous contaminant test solutions were continuously stirred at low speed prior to entry into the glass column to maintain a homogenous composition. During the tenth bed volume, an effluent sample from each column was collected and analyzed for the particular aqueous contaminant. Additionally, a single influent sample for each test was collected and analyzed for the contaminant concentration.

The results of these tests are set forth in Table 3 below.

TABLE 3					
PARTICLE DESIG- NATION	AQUEOUS CON- TAMINANT	INFLUENT	EFFLUENT	FLOW RATE	DETECTION LIMIT
1t	Arsenic	2,890 ppb	< 10 ppb	5-6 GPM/ft ²	10 ppb
1u	Cadmium	1,003 ppb	<10 ppb	5-6 GPM/ft ²	10 ppb
1v	Chlorine	263 ppb	<10 ppb	5-6 GPM/ft ²	10 ppb
1w	DBCP 1,2-Dibromo- 3- Chloropropane	(sw) 230.0 μg/l (sw) 210.0 μg/l (gw) 0.07 μg/l	<0.02 μg/l <0.02 μg/l <0.02 μg/l	5-6 GPM/ft ² 5-6 GPM/ft ² 5-6 GPM/ft ²	0.02 μg/l 0.02 μg/l 0.02 μg/l
1x	Iron	1.15 mg/l	<0.03 mg/l	5-6 GPM/ft ²	0.03 μg/l
1y	Lead	215 ppb	< 10 ppb	5-6 GPM/ft ²	10 ppb
1z	Phosphates	40.45 mg/l	9.50 mg/l	5-6 GPM/ft ²	N/A
1aa	Radon	1,104.2 pCi/l 911.6 pCi/l	303.2 pCi/l 306.1 pCi/l	5-6 GPM/ft ² 5-6 GPM/ft ²	N/A

sw = Synthetic water
gw = ground water

Example 4

A particle of 100% activated carbon coconut (non-acid treated) was irradiated by the ion-beam in accordance with the procedures of step (ii) of Example 1. An ESCA spectrometer was used to analyze the surface composition for the original activated carbon particle and the particle after it was irradiated by the ion beam. The surface characterization results are as follows.

TABLE 4		
ELEMENT	INITIAL ACTIVATED CARBON PARTICLE (Atom %)	ACTIVATED CARBON PARTICLE OF THIS INVENTION (Atom %)
Carbon	96.47	61.65
Oxygen	3.53	16.37
Sodium		0.59
Fluorine		8.61
Potassium		7.60
Chlorine		1.61
Sulfur		0.86
Phosphorus		0.55
Magnesium		2.5

Thus, the initial particle had an oxygen/carbon ratio of about 0.04, whereas the treated activated carbon particle of this invention had an oxygen/carbon ratio of about 0.27, for an increased oxygen/carbon ratio of about 7 times the original. A similar test was run on 100% aluminum oxide prepared according to the process of Example 1. The oxygen/aluminum ratio was increased at least about 2 fold over the original untreated particle oxygen/aluminum ratio.

Example 5

A TCLP test was run on two different contaminant remediation applications of this invention. The particles were prepared by step (ii) of Example 1 and were used to adsorb the particular contaminants in Table 5 below. In accordance with the EPA test methods, the particles were, *inter alia*, washed with an acid solution and tumbled for the requisite length of time. The concentration of the contaminants removed from the particle were then measured. The results are set forth below in Table 5.

TABLE 5				
PARTICLE	CONTAMINANT	EPA TCLP TEST METHOD	TCLP CONTAMINANT (mg/l)	PQL ¹
100% Al ₂ O ₃	Lead	1311/6010	< 0.50	0.50
100% Al ₂ O ₃	Phosphate	1311/365.4	<0.1	0.1

¹ PQL is the practical quantitation limit, which is an EPA standard, and is different than the lowest detectable limit.

Thus, the particles of the invention, when acting as an adsorbent, bond tightly to the contaminants.

Example 6

Two fixed bed reactors were charged with 158 g, 9.4 cubic inches (2 inches diameter x 3 inches high) of 1n [10% Al₂O₃, 5% CuO, 45% MnO₂, 37% zeolite (Zeolyst international CBV), 3% PVP (GAF PVP K-60 polyvinylpyrrolidinone)] and this same particle, except that it was not irradiated by the ion beam (designated as 1n'- control for 1n). A mixture of 101.8 ppm NO and 1,035 ppm CO in air was fed into each fixed bed reactor at room temperature at a rate of 35 standard cubic feet per hour (SCFH). The effluent of the fixed bed reactor was fed into a Horiba CLA-510SS NO_x analyzer and a VIA-510 CO analyzer. The NO concentration dropped immediately reaching 5.4 ppm by 5 minutes with 1n (the first recorded measurement) and continued to drop to 4.0 ppm by 40 min. (See, Figure 2). The CO concentration dropped more slowly, dropping to 532 ppm at 40 min. (See, Figure 3). The test was stopped shortly after 40 minutes. The CO concentration was still decreasing at 40 min. and may decrease further upon further reaction time. In the case of 1n', the NO concentration dropped below 10 ppm after the first five minutes (See, Figure 4); however, the concentration

rose steadily the next 25 minutes until it leveled off at approximately 105 ppm, which was very close to the initial NO concentration. It is believed that the particles of the invention catalytically degrade the CO and NO.

Example 7

Various adsorbent and/or catalytic binder systems as set forth in Table 6 in Example 8 below were made in accordance with the general procedures of this invention as follows as well as various systems not a part of the invention.

5

The binder and adsorbent and/or catalytic particles were combined into a mixing vessel, the amount of each varied according to the size batch desired. However, the component ratios remained constant as indicated in Table 6 below. This "dry" combination was pre-mixed to ensure a homogenous mixture of all of the components. After this was accomplished, a solution containing 5% acetic acid in distilled water was added to the mixture. The amount of the acid compared to the other components varied depending on extruding parameters and other processing variables, but for the procedures herein the range was typically between 35 and 45 wt. % of the total mixture.

10

This solution was added to the dry materials and mixed until the material had a homogenous "modeling clay" like consistency. The mixing was performed utilizing a Hobart "A-300" mixer. The material was then ready for extrusion. The mixed product containing the acetic acid solution was fed through an extruder, such as a DGL-1 dome granulator manufactured by LCI Corporation of Charlotte, N.C., U.S.A. The extrudates were fed through a QJ-230 marumarizer, also manufactured by LCI Corporation, which turned the extrudates as "Rods" into small spheres. The extruding and marumarizing steps provided a finished product suitable to use for a specific application. However, the marumarizing is optional and does not alter the performance of the product. After the spheres were made, the product was transferred to a drying oven where it was dried for one (1) hour at a temperature of 250° Celsius. The product was then ready for use in an application.

15

20

25

Example 8

The particles as formed of the constituents listed below in Table 6 were tested for their ability to remove TCE. Adsorbent and/or catalyst and binder systems of Table 6 were

30

challenged with various concentrations of TCE as indicated in Table 6. Two custom made columns (40 cm X 20 mm) equipped with coarse glass frits were dried packed with 10 mL volumes (measured with a 10 mL graduated cylinder) of particles. The columns were challenged with five 10 mL aliquots (5 bed volumes) of the trichloroethylene (TCE) solution. The fifth bed volume from each column was collected in a 50 mL Erlenmeyer flask, stoppered, and immediately analyzed by purge and trap-GC/MS technique using a Finnigan MAT
5 Magnum ion trap GC/MS equipped with a Tekmar liquid sample concentrator (LSC 2000).

The particles in Table 6 were prepared as described in Example 7. The percent composition of each component as well as the nature of the binder are presented in Table 6.
10 Prior to mixing with the other components, the aluminum oxide particle was first calcined at 500°C or 550°C as indicated in Table 6, then acid treated by substantially contacting with 0.5% acetic acid at room temperature for 15 minutes as generally set forth in applicants' copending application filed on even date entitled "Acid Contacted Enhanced Adsorbent Particle and Method of making and Using Therefor" and as set forth in the parent applications
15 to that application as listed above, and then dried at 121°C for 90 minutes.

The removal of TCE from aqueous solution was investigated using a number of adsorbent and/or catalyst and binder systems of the present invention, and these results are summarized in Table 6. In Entry 8, 99% reduction of TCE was observed when the particle
20 consisted of 40% CuO, 40% MnO₂, and 20% colloidal alumina as the binder. When no binder was used, however, the CuO/MnO₂ particle removed only 0-1% of TCE (Entries 9A 9B). These results indicate the necessity of the binder material to enhance or provide adsorbent and/or catalytic properties of or to the particle. Other particles demonstrated the ability to remove TCE. For example, entry 1 removed > 95% of TCE. Entry 7 removed 99% of TCE.
25 The particle of entry 7 had two adsorbent and/or catalyst particles, one of which was carbon. Carbon was also used in conjunction with multiple metal oxide components (Entry 24A and B) to remove TCE (>90%).

Although Entry 3 removed 96% of TCE, the PVP binder does not hold the particle
30 together as long as the binders of the present invention. Particles with the PVP binder

disintegrated over time, which reduced the usefulness of the particle. In the case of Entries 5A, 5B and 6, TCE removal was very high (98%); however, the activated peat also breaks apart much faster than the particles of the present invention. The contaminants adsorbed by the peat may also leach into the environment.

5 Not wishing to be bound by theory, two plausible mechanisms can account for the catalytic degradation of TCE using the particles of the present invention. The first mechanism involves redox chemistry between TCE and the metal oxide components of the particle. TCE is electrophilic, and can stabilize a negative charge if reduced. Electron transfer from a metal oxide component to TCE may be the first step toward the degradation of TCE. A second
10 mechanism involves a Lewis acid-base interaction between TCE and the metal oxide component, which increases the rate of nucleophilic attack of TCE by water. Due to the lone pair electrons on the chlorine groups of TCE, a metal oxide component can initially coordinate to the chlorine group. This initial coordination may also be the first step toward the catalytic degradation of TCE.

15

Table 6

Entry	Binder (Wt %)	Drying/ Crosslinking temperature °C (time min)	Al ₂ O ₃ wt% (Calcining temperature, °C), Acid treated	CuO (Wt %)	MnO ₂ (Wt %)	Other Component(s) (wt %)	TCE influent concentration Run A	TCE effluent concentration 5th bed volume (%) reduction Run A	TCE influent concentration Run B	TCE effluent concentration 5th bed volume (%) reduction Run B
1	V-900 (20)	150 (15)	70 (550)	5	5		1.0 ppm	< 50 ppb (>95%)		
2	PVP (3.2)	150 (30)	91.3 (550)	2.5	2.5	Methyl/Cellulose (0.5)	50.0 ppm	29.4 ppm (59)	5.0 ppm	0.5 ppm (90)
3	PVP (3.2)	150 (30)	91.3 (550)	2.5	2.5	Methyl/Cellulose (0.5)	5.0 ppb	0.20 ppb (96)		
4		NA				Zeolite (100)	rejected*			
5		NA				Acid treated Peat (100)	50.0 ppm	1.0 ppm (98)	5.0 ppm	0.1 ppb (98)
6		NA				Acid treated Peat (100)	5.0 ppb	0.07 ppb (98)		
7	V-900 (20)	250 (60)	40 (500)			WPH Carbon (40)	5.0 ppb	0.06 ppb (99)		
8	V-900 (20)	250 (60)		40	40		5.0 ppb	0.07 ppb (99)		

9		250 (60)		50	50		50.0 ppb	50.4 ppb (0)	50.0 ppm	49.6 ppm (1)
10	V-900 (20)	250 (60)	60 (500)	10	10		50 ppm	39.5 ppm (21)	50.0 ppb	39.9 ppm (20)
11	V-900 (20)	250 (60)	70 (500)	5	5		50.0 ppm	39.3 ppm (21)	50.0 ppb	45.8 ppm (8)
12	V-900 (20)	250 (60)		10	10	Zeolite (60)	50.0 ppm	37.2 ppm (26)	50.0 ppb	41.0 ppb (18)
13		250 (60)	100 (550)				50.0 ppm	21.2 ppm (58)	50.0 ppb	34.0 ppb (32)
14	V-900 (20)	250 (60)	67 (550)	5	5		rejected**			
15	PVP (3) V-900 (20)	250 (60)	71.6 (550)	2.5	2.5	MethylCellulose (0.4)	rejected**			
16	PVP (3) V-900 (17)	250 (60)	13.6 (550)	1.7	1.7	Tin (66)	rejected**			
17	V-900 (13.6)	250 (60)	17 (550)	1.7	1.7	Zinc (66)	rejected**			
18	V-900 (13.6)	250 (60)	17 (550)	1.7	1.7		50.0 ppm	42.8 ppm (14)	50.0 ppb	44.4 ppb (11)
19	V-900 (20)	250 (60)	17 (550)	1.7	1.7	Tin (66)	50.0 ppm	36.3 ppm (27)	50.0 ppb	41.9 ppb (16)
20	V-900, (20)	250 (60)	17 (550)	1.7	1.7	Zinc (59.6)	50.0 ppm	27.8 ppm (44)	50.0 ppb	27.0 ppb (46)

21	V-900 (20)	250 (60)	70 (550)	5	5		50.0 ppm	24.8 ppm (50)	50.0 ppb	17.5 ppb (65)
22	V-900 (20)	550 (60)	70 (550)	5	5#		50.0 ppm	42.7 ppm (15)	50.0 ppb	20.3 ppb (59)
23		NA				WPH Carbon (100)	rejected*			
24	V-900 (19.9)	250 (60)	59.7 (550)	5.98	4.98	WPH Carbon (9.95) Avicel Cellulose (0.5)	50.0 ppm	<5.0 ppm (>90)	50.0 ppb	3.9 ppb (92)
25	Sol P2 (20)	250 (60)	70 (550)	5	5		50.0 ppm	5.8 ppm (88)	50.0 ppb	11.3 ppb (77)

* sample did not allow water flow

** particle fell apart upon use

PVP = GAF PVP K-60 Polyvinylpyrrolidone V-900 = LaRoche V-900 gel alumina (colloidal alumina)

Sol P2 = Condea Disperal Sol P2 (colloidal alumina)

Zeolite = Zeolyst international CBV 100CuO = Fisher C472

MnO₂ = Kerr-

McGee KM® Electrolytic Manganese Dioxide 92 % MnO₂ X-ray powder diffraction studies indicate this to be a mixture of manganese oxides.

Tin = Fisher T128 Zinc = Fisher Z16

MethyICellulose = Fisher M352

WHP Carbon = Calgon WPH powdered activate carbon# particle heated to 550° C in air to convert MnO₂ to

Mn₃O₄

NA = not applicable

Example 9

Various adsorbent and/or catalyst and binder systems of Table 7 were prepared according to the procedures of Examples 7 and Example 8 (aluminum oxide preparation). Samples were tested to determine if they reacted with hydrogen sulfide at room temperature. Hydrogen sulfide was generated by treating sodium sulfide with sulfuric acid and vacuum transferred into an IR cell which had been loaded with 1.00 g of adsorbent and/or catalyst binder system to be tested. The IR cell used was 9 cm long by 4 cm in diameter (~120 mL volume). The cell was filled to approximately 170 torr H₂S and observed visually and IR spectra recorded.

The percent composition of each component as well as the nature of the binder are presented in Table 7. The aluminum oxide particle was first calcined at 550°, then acid washed using 0.5% acetic acid and dried at 121°C for 90 minutes using the same procedure described in Example 8. The cross-linking temperature for each particle was 250°C for 1 hour.

The removal of hydrogen sulfide using the adsorbent and/or catalyst and binder systems of the present invention was investigated, and these results are summarized in Table 7. The removal of hydrogen sulfide by the adsorbent and/or catalyst binder systems was monitored by infrared spectroscopy. Based on these results, adsorbent and/or catalyst and binder systems of colloidal aluminum binder, acid treated aluminum oxide, and copper oxide provided the best results with regards to the removal of hydrogen sulfide.

Table 7

Entry	Binder (Wt %)	Al ₂ O ₃ wt%	ZnO wt %	CuO wt %	Length of Experiment to Remove H ₂ S	H ₂ S reacted	Comments
1	V-900 (40)	50	10		16 h	Yes	Virtually all absorbed as determined IR
2	V-900 (50)	40	10		24 h	Yes	Virtually all absorbed as determined IR
3	V-900 (60)	30	10		42 h	Yes	Discoloration observed after 4 h Virtually all absorbed as determined IR
4	V-900 (20)	60	10	10	24 h	Yes	Virtually all absorbed as determined IR
5	V-900 (20)	60	20		2 h	Yes	Discoloration observed after 2 h Virtually all absorbed as determined IR
6	V-900 (25)	70		5	2 h	Yes	Discoloration observed after 2 h Virtually all absorbed as determined IR
7	V-900 (38)	60		2	3 h	Yes	Discoloration observed after 3 h Virtually all absorbed as determined IR

8	V-900 (30)	50		20	1.5 h	Yes	Discoloration observed after 1.5 h Virtually all absorbed as determined IR
9	V-900 (30)	20		50	16.5 h	Yes very slowly	Very slow little change after 2 h
10	V-900 (30)	69		1	4 h	Yes	Discoloration observed after 2 h Virtually all absorbed as determined IR

Al_2O_3 = calcined at 550°C and then acid treated

V-900 = LaRoach V-900 gel alumina (colloidal alumina)

Example 10

TCE adsorption and TCLP extraction procedures were performed as follows. A 20.0114-gram (about 24.50 mL bed volume) sample of the colloidal alumina and $\text{Al}_2\text{O}_3/\text{CuO}/\text{MnO}_2$ combination particle of Table 7, entry 1, after treatment with TCE was wet packed into a 50-mL buret (with removable stopcock) plugged with glass wool. The sample was charged with five bed volumes of water. The sorbent material was then quantitatively transferred into the Zero Headspace Extractor (ZHE) apparatus into which 200 mL of water was added, appropriately sealed and agitated for 18 hours. The filtered solution was collected in two 100 mL vials, stored in the refrigerator at 4°C until analysis by GC/MS. The Finnigan MAT Magnum ion trap GC/MS equipped with a Tekmar liquid sample concentrator (LSC 2000) was used for analysis.

The calibration curve procedure was as follows. A freshly prepared 50 ppm TCE stock solution was obtained by dissolving 34.2 μL spectrophotometric grade TCE (Aldrich) in 20 mL HPLC grade methanol (Fisher) followed by dilution to a liter. Dilution of this solution (1000 μL : 1L) resulted in a 50 ppb TCE stock solution. All dilutions were accomplished using deionized water. A calibration curve was constructed by purging 1.0, 0.50, 0.20, 0.10, and 0.050 ppb TCE solutions.

The results are set forth below in Table 3.

TABLE 3		
Sorbent Sample	TCE found, ppb	TCE Detection limit, ppb
Table 7, entry 1	Nd ^a	0.0050

^a = Not detected. The fact that TCE in the sample is less than 500 ppb (EPA TCLP limit) characterizes it as a nonhazardous waste with respect to TCE.

Throughout this application, various publications are referenced. The disclosures of these publications in their entireties are hereby incorporated by reference into this application in order to more fully describe the state of the art to which this invention pertains.

It will be apparent to those skilled in the art that various modifications and variations can be made in the present invention without departing from the scope or spirit of the invention. Other embodiments of the invention will be apparent to those skilled in the art from consideration of the specification and practice of the invention disclosed herein. It is intended that the specification and examples be considered as exemplary only, with a true scope and spirit of the invention being indicated by the following claims.

What is claimed is:

1. A method for producing an enhanced adsorbent and/or enhanced catalytic particle and/or for producing a catalytic particle, comprising the steps of:
 - (a) removing an effective amount of air from a closed chamber containing an adsorbent and/or catalytic particle, wherein the resultant chamber pressure is less than one atmosphere;
 - (b) raising the chamber pressure with an inert gas to at least one atmosphere;
 - (c) contacting the particle with an energy beam of sufficient energy for a sufficient time to thereby enhance the adsorbent and/or catalytic properties of the particle and/or produce catalytic properties in the particle.
2. The method of Claim 1, wherein the particle comprises an oxide particle or activated carbon.
3. The method of Claim 1, wherein the particle comprises an oxide of metal, an oxide of silicon or activated carbon.
4. The method of Claim 1, wherein the particle comprises aluminum oxide, titanium dioxide, copper oxide, vanadium pentoxide, silicon dioxide, manganese dioxide, iron oxide, zinc oxide, activated carbon, or zeolite.
5. The method of Claim 1, wherein the particle comprises aluminum oxide.
6. The method of Claim 5, further comprising a second particle of titanium dioxide, copper oxide, vanadium pentoxide, silicon dioxide, manganese dioxide, iron oxide, zinc oxide, activated carbon, or zeolite.

7. The method of Claim 1, wherein the particle comprises aluminum oxide and activated carbon.
8. The method of Claim 7, wherein the particle further comprises silicon dioxide and wherein the activated carbon is a mixture of coal based and coconut based activated carbon.
9. The method of Claim 1, wherein the particle is an agglomeration of smaller particles and a binder.
10. The method of Claim 9, wherein the smaller particles are of different composition type.
11. The method of Claim 1, wherein in step (b) the chamber gauge pressure is from 1 psi to 5,000 psi.
12. The method of Claim 1, wherein in step (b) the chamber gauge pressure is at least 100 psi, and further comprising after step (c), rapidly decompressing the chamber pressure to thereby increase the surface area of the particle.
13. The method of Claim 12, wherein in step (b) the chamber gauge pressure is at least 5,000 psi.
14. The method of Claim 1, wherein the inert gas is argon.
15. The method of Claim 1, wherein the energy beam is an ion or electron beam.
16. The method of Claim 1, wherein the method produces a room temperature catalytic particle.

17. A method for producing an enhanced adsorbent and/or enhanced catalytic particle and/or for producing a catalytic particle, comprising implanting oxygen into an adsorbent and/or catalytic particle.
18. The method of Claim 17, wherein the method produces a room temperature catalytic particle.
19. The method of Claim 17, further comprising increasing the electrical charge on the particle.
20. The particle made by the process of Claim 1.
21. The particle made by the process of Claim 4.
22. The particle made by the process of Claim 5.
23. The particle made by the process of Claim 6.
24. The particle made by the process of Claim 12.
25. The particle made by the process of Claim 17.
26. An enhanced adsorbent and/or enhanced catalytic particle and/or a catalytic particle comprising an adsorbent particle that has been treated to provide an excess of oxygen implanted at least on the surface of the particle to thereby form an enhanced adsorbent and/or enhanced catalytic particle and/or a catalytic particle.
27. The oxygen implanted particle of Claim 26, wherein the oxygen implanted particle has at least 1.5 times the oxygen atom per cent to non-oxygen atom per

cent ratio at its surface compared to the initial non-oxygen implanted particle, said surface characterization being determined by an ESCA spectrometer.

28. The oxygen implanted particle of Claim 26, wherein the particle comprises activated carbon and the oxygen implanted carbon has at least 6 times the oxygen to carbon ratio compared to the initial non-oxygen implanted carbon.
29. The oxygen implanted particle of Claim 26, wherein the particle comprises aluminum oxide and the oxygen implanted aluminum oxide has at least two times the oxygen to aluminum ratio compared to the initial non-oxygen implanted aluminum oxide.
30. A binder for binding adsorbent and/or catalytic particles to produce an agglomerated particle comprising colloidal aluminum oxide and an acid.
31. The binder of Claim 30, wherein the acid is nitric acid.
32. A method for binding adsorbent and/or catalytic particles, comprising the steps of:
 - (a) mixing colloidal aluminum oxide with the particles and an acid;
 - (b) agitating the mixture to homogeneity; and
 - (c) heating the mixture for a sufficient time to cause cross-linking of the aluminum oxide in the mixture.
33. The method of Claim 32, wherein the colloidal aluminum oxide is from 20% to 99% by weight of the mixture.
34. The method of Claim 32, wherein the acid is nitric acid.
35. A method for reducing or eliminating the amount of a contaminant from a liquid

or gas stream comprising contacting the particle of Claim 20 with the contaminant in the stream for a sufficient time to reduce or eliminate the amount of contaminant from the stream.

36. The method of Claim 35, wherein the stream is a liquid.
37. The method of Claim 35, wherein the stream is water.
38. The method of Claim 35, wherein the stream is a gas.
39. The method of Claim 35, wherein the stream is air.
40. The method of Claim 35, wherein the contaminant is an organic compound.
41. The method of Claim 35, wherein the contaminant is a heavy metal.
42. The method of Claim 35, wherein the contaminant is carbon monoxide or an oxide of nitrogen or sulfur.
43. The method of Claim 35, wherein the contaminant is acetone, ammonia, benzene, carbon monoxide, chlorine, 1,4-dioxane, ethanol, ethylene, formaldehyde, hydrogen cyanide, hydrogen sulfide, methanol, methyl ethyl ketone, methylene chloride, nitrogen oxide, propylene, styrene, sulfur dioxide, toluene, vinyl chloride, arsenic, cadmium, chlorine, DBCP, iron, lead, phosphate, radon, selenium, or uranium.
44. A method for adsorbing a contaminant from a liquid or gas stream onto an adsorbent particle comprising contacting the particle of Claim 20 with the contaminant in the stream for a sufficient time to adsorb the contaminant.

45. A method for catalyzing the degradation of a hydrocarbon comprising contacting the hydrocarbon with the particle of Claim 20 for a sufficient time to catalyze the degradation of the hydrocarbon.
46. The method of Claim 45, wherein the catalysis reaction is at room temperature.
47. A method for reducing or eliminating the amount of a contaminant from a gas stream by catalysis comprising contacting the particle of Claim 20 with a gas stream containing a contaminant comprising an oxide of nitrogen, an oxide of sulfur, carbon monoxide, or mixtures thereof for a sufficient time to reduce or eliminate the contaminant amount.
48. The method of Claim 47, wherein the catalysis reaction is at room temperature.
49. The method of Claim 47, wherein the contaminant comprises an oxide of nitrogen or carbon monoxide.
50. An apparatus for producing an enhanced adsorbent and/or enhanced catalytic particle and/or for producing a catalytic particle comprising:
 - (a) chamber means for containing the particle in a closed system having an inlet gas port, an exit gas port, and a target plate, said chamber means being capable of maintaining vacuum and positive pressures;
 - (b) means for providing an inert gas to the chamber means through the inlet gas port;
 - (c) means for withdrawing from the chamber means an effective amount of the ambient air therein so as to create a vacuum within the chamber means; and
 - (d) means for providing an energy beam to the chamber means, said energy beam means outlet being targeted at the target plate.

51. The apparatus of Claim 50, wherein the energy beam means produces an ion or electron beam.
52. A method for increasing the surface area of an adsorbent and/or catalytic particle, comprising the steps of
 - (a) raising the chamber gauge pressure of a closed chamber containing the adsorbent and/or catalytic particle to at least 100 psi with an inert gas and
 - (b) rapidly decompressing the chamber pressure to thereby increase the surface area of the particle.
53. The method of Claim 52, wherein the pressure in step (a) is at least 5,000 psi.
54. The method of Claim 52, wherein the surface area is increased by at least 20%.
55. A method for producing an enhanced adsorbent and/or enhanced catalytic particle and/or for producing a catalytic particle, comprising the step of:
 - (a) contacting an adsorbent and/or catalytic particle with an energy beam of sufficient energy for a sufficient time to thereby enhance the adsorbent and/or catalytic properties of the particle and/or produce catalytic properties in the particle.
56. The method of Claim 55, wherein the process is continuous.
57. The method of claim 1, wherein the sufficient energy is from 1 to 100 eV.
58. The method of claim 1, wherein the sufficient energy is from 15 to 25 eV.
59. The method of claim 1, wherein the adsorbent and/or catalytic particle comprises at least two types of particles and further comprises a binder

comprising colloidal metal oxide or colloidal metalloid oxide.

60. The method of claim 59, wherein the binder is cross-linked to at least one of the particle types or to itself.
61. The method of claim 1, further comprising after step (c),
 - (d) mixing the particle with at least one other type of adsorbent and/or catalyst particle, a binder comprising colloidal metal oxide or colloidal metalloid oxide, and an acid; and
 - (e) heating the mixture to a sufficient temperature for a sufficient time to cross-link the binder to at least one type of particle or to itself.
62. The particle of claim 20, wherein the adsorbent and/or catalytic particle comprises at least two types of particles made by the process of claim 1 and further comprises a binder comprising colloidal metal oxide or colloidal metalloid oxide.
63. The particle of claim 62, wherein the binder is cross-linked to at least one of the particle types or to itself.
64. An adsorbent and/or catalyst and binder composition comprising the particle made by the process of claim 1 and further comprising a second type of adsorbent and/or catalyst particle and a binder comprising colloidal metal oxide or colloidal metalloid oxide.
65. The composition of claim 64, wherein the binder is cross-linked to at least one of the particle types or to itself.
66. The method of claim 5, wherein the aluminum oxide is a non-amorphous, non-ceramic, crystalline, porous, calcined, aluminum oxide particle that was

produced by calcining at a particle temperature of from 400° C to 700° C.

1/4




FIG. 1

2/4




FIG. 2





FIG. 3

4/4

**FIG.4**

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US97/18729

A. CLASSIFICATION OF SUBJECT MATTER

IPC(6) : Please See Extra Sheet.

US CL : Please See Extra Sheet.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : Please See Extra Sheet.

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X ----- Y	US 3,485,771 A (HORVATH) 23 December 1969 (29-12-69), column 2, line 11 through column 3, line 19.	55 ----- 1-16, 20-24, 35- 44, 47-51, 56-66
X ----- Y	US 4,764,394 A (CONRAD) 16 August 1988, Abstract, column 1, lines 18-29, column 2, lines 18-21 and 49-54.	55 ----- 54-66
Y	US 4,874,596 A (LEMELSON) 17 October 1989 (17-10-89), the whole document.	1-16, 20-24, 35- 44, 47-51, 55-66
X ----- Y	US 4,885,065 A (GILGENBACH) 05 December 1989 (05-12-89), column 4, lines 18-60, column 5, lines 10-49, and column 7, lines 24-40.	55 ----- 56-66

☒ Further documents are listed in the continuation of Box C.
 ☐ See patent family annex.

* Special categories of cited documents:	*T	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
A document defining the general state of the art which is not considered to be of particular relevance	*X*	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
E earlier document published on or after the international filing date	*Y*	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*Z*	document member of the same patent family
O document referring to an oral disclosure, use, exhibition or other means		
P document published prior to the international filing date but later than the priority date claimed		

Date of the actual completion of the international search

12 JANUARY 1998

Date of mailing of the international search report

02 FEB 1998

 Name and mailing address of the ISA/US
 Commissioner of Patents and Trademarks
 Box PCT
 Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

IN SUK BULLOCK

Telephone No. (703) 308-0661

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US97/18729

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 4,943,356 A (DIETRICH) 24 July 1990 (24-07-90), column 3, lines 28-56 and column 4, line 28 through column 5, line 54.	50-51
Y	US 5,204,070 A (WILSON ET AL) 20 April 1993 (20-04-93), abstract and column 4, line 38 through column 9, line 34.	1-16, 20-24, 35-44, 47-51, 55-66
Y	US 5,238,888 A (ABE) 24 August 1993 (24-08-93), column 3, line 46 through column 5, line 37.	1-16, 20-24, 35-44, 47-51, 55-66
X	US 5,414,204 A (HOSONO ET AL) 09 May 1995 (09-05-95), Abstract.	55
Y	WO 94/26661 A1 (HOLLAND ET AL) 24 November 1994 (24-11-94), pages 2-4.	1-16, 20-24, 35-44, 47-51, 55-66

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US97/18729

Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This international report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:

2. ☐ Claims Nos.:
because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically:

3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

1. ☐ As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims for which fees were paid, specifically claims Nos.:

4. ☒ No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:
1-16, 20-24, 35-44, 47-51 and 55-66

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
☐ No protest accompanied the payment of additional search fees.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US97/18729

A. CLASSIFICATION OF SUBJECT MATTER:

IPC (6):

B01D 15/04, 53/02; B01J 8/00, 5/02, 19/08, 20/00, 20/02, 20/10, 20/20, 23/00, 23/02, 23/32, 23/70, 29/06, 37/34; C01B 7/00, 17/16, 53/00; C02F 1/42; C07C 1/00

A. CLASSIFICATION OF SUBJECT MATTER:

US CL :

502/5, 64, 68, 324, 338, 343, 345, 350, 406, 407, 413, 415, 417, 437, 523; 204/157.15, 157.44; 210/688, 690, 691, 694; 95/91, 129, 132, 136, 137, 140, 143, 147; 423/213.2, 230, 231, 239.1, 239.2, 240R, 241, 244.01, 244.09, 244.11, 247; 422/186

B. FIELDS SEARCHED

Minimum documentation searched

Classification System: U.S.

502/5, 64, 68, 324, 338, 343, 345, 350, 406, 407, 413, 415, 417, 437, 523; 204/157.15, 157.44; 210/688, 690, 691, 694; 95/91, 129, 132, 136, 137, 140, 143, 147; 423/213.2, 230, 231, 239.1, 239.2, 240R, 241, 244.01, 244.09, 244.11, 247; 422/186